



09-07-00

PTO/SB/05 (4/98)

Approved for use through 09/30/2000. OMB 0651-0032

Patent and Trademark Office: U.S. DEPARTMENT OF COMMERCE

Please type a plus sign (+) inside this box →

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

UTILITY PATENT APPLICATION TRANSMITTAL

(Only for new nonprovisional applications under 37 C.F.R. § 1.53(b))

Attorney Docket No. **D/A0306II**First Inventor or Application Identifier **Donald R. Titterington**Title **See 1 in Addendum**Express Mail Label No. **EL465688165****APPLICATION ELEMENTS**

See MPEP chapter 600 concerning utility patent application contents.

1. * Fee Transmittal Form (e.g., PTO/SB/17)
(Submit an original and a duplicate for fee processing)
2. Specification [Total Pages **52**]
(preferred arrangement set forth below)
 - Descriptive title of the Invention
 - Cross References to Related Applications
 - Statement Regarding Fed sponsored R & D
 - Reference to Microfiche Appendix
 - Background of the Invention
 - Brief Summary of the Invention
 - Brief Description of the Drawings (if filed)
 - Detailed Description
 - Claim(s)
 - Abstract of the Disclosure
3. Drawing(s) (35 U.S.C. 113) [Total Sheets **1**]
4. Oath or Declaration [Total Pages **5**]
 - a. Newly executed (original or copy)
 - b. Copy from a prior application (37 C.F.R. § 1.63(d))
(for continuation/divisional with Box 16 completed)
 - i. DELETION OF INVENTOR(S)
Signed statement attached deleting inventor(s) named in the prior application, see 37 C.F.R. §§ 1.63(d)(2) and 1.33(b).

*NOTE FOR ITEMS 1 & 13 IN ORDER TO BE ENTITLED TO PAY SMALL ENTITY FEES, A SMALL ENTITY STATEMENT IS REQUIRED (37 C.F.R. § 1.27), EXCEPT IF ONE FILED IN A PRIOR APPLICATION IS RELIED UPON (37 C.F.R. § 1.28).

ADDRESS TO: Assistant Commissioner for Patents
Box Patent Application
Washington, DC 20231

5. Microfiche Computer Program (Appendix)
6. Nucleotide and/or Amino Acid Sequence Submission
(if applicable, all necessary)
 - a. Computer Readable Copy
 - b. Paper Copy (identical to computer copy)
 - c. Statement verifying identity of above copies

ACCOMPANYING APPLICATION PARTS

7. Assignment Papers (cover sheet & document(s))
8. 37 C.F.R. § 3.73(b) Statement Power of (when there is an assignee) Attorney
9. English Translation Document (if applicable)
10. Information Disclosure Statement (IDS)/PTO-1449 Copies of IDS Citations
11. Preliminary Amendment
12. Return Receipt Postcard (MPEP 503)
(Should be specifically itemized)
 - * Small Entity Statement(s) Statement filed in prior application (PTO/SB/09-12)
 - 13. Certified Copy of Priority Document(s) (if foreign priority is claimed)
 - 14. Other:
.....
 - 15. Other:
.....

16. If a CONTINUING APPLICATION, check appropriate box, and supply the requisite information below and in a preliminary amendment:

Continuation Divisional Continuation-in-part (CIP) of prior application No: **09 / 078,190**

Prior application information: Examiner _____ Group / Art Unit: _____

For CONTINUATION or DIVISIONAL APPS only: The entire disclosure of the prior application, from which an oath or declaration is supplied under Box 4b, is considered a part of the disclosure of the accompanying continuation or divisional application and is hereby incorporated by reference. The incorporation can only be relied upon when a portion has been inadvertently omitted from the submitted application parts.

17. CORRESPONDENCE ADDRESS

<input checked="" type="checkbox"/> Customer Number or Bar Code Label /	021567			or <input type="checkbox"/> Correspondence address below
(Insert Customer No. or Attach bar code label here)				
Name				
Address				
City	State		Zip Code	
Country	Telephone		Fax	

Name (Print/Type)	David G. Latwesen, Ph.D.	Registration No. (Attorney/Agent)	38,533
Signature		Date	9/15/00

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Box Patent Application, Washington, DC 20231.

EL465688165

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

FEE TRANSMITTAL for FY 1999

Patent fees are subject to annual revision.

Small Entity payments must be supported by a small entity statement, otherwise large entity fees must be paid. See Forms PTO/SB/09-12.TOTAL AMOUNT OF PAYMENT (\$)
1,864.00

Complete if Known

Application Number	PTO 841 U.S. 654735 09/05/00
Filing Date	
First Named Inventor	Donald R. Titterington
Examiner Name	
Group / Art Unit	
Attorney Docket No.	D/A0306II

METHOD OF PAYMENT (check one)

1. The Commissioner is hereby authorized to charge indicated fees and credit any overpayments to:

Deposit Account Number
24-0037Deposit Account Name
Xerox Corporation Charge Any Additional Fee Required Under 37 CFR 1.16 and 1.17

2. Payment Enclosed:
 Check Money Order Other

FEE CALCULATION

1. BASIC FILING FEE

Large Entity Fee Code (\$)	Small Entity Fee Code (\$)	Fee Description	Fee Paid
101 760	201 380	Utility filing fee	690
106 310	206 155	Design filing fee	
107 480	207 240	Plant filing fee	
108 760	208 380	Reissue filing fee	
114 150	214 75	Provisional filing fee	
SUBTOTAL (1) (\$)			690.00

2. EXTRA CLAIM FEES

Total Claims	Extra Claims	Fee from below	Fee Paid
44	-20** = 24	x 18	= 432
Independent Claims 12	-3*** = 9	x 78	= 702
Multiple Dependent			= 0.00

** or number previously paid, if greater; For Reissues, see below

Large Entity Fee Code (\$)	Small Entity Fee Code (\$)	Fee Description
103 18	203 9	Claims in excess of 20
102 78	202 39	Independent claims in excess of 3
104 260	204 130	Multiple dependent claim, if not paid
109 78	209 39	** Reissue independent claims over original patent
110 18	210 9	** Reissue claims in excess of 20 and over original patent
SUBTOTAL (2) (\$)		1,134.00

3. ADDITIONAL FEES

Large Entity Fee Code (\$)	Small Entity Fee Code (\$)	Fee Description	Fee Paid
105 130	205 65	Surcharge - late filing fee or oath	0.00
127 50	227 25	Surcharge - late provisional filing fee or cover sheet	0.00
139 130	139 130	Non-English specification	0.00
147 2,520	147 2,520	Forfiling a request for reexamination	0.00
112 920*	112 920*	Requesting publication of SIR prior to Examiner action	0.00
113 1,840*	113 1,840*	Requesting publication of SIR after Examiner action	0.00
115 110	215 55	Extension for reply within first month	0.00
116 380	216 190	Extension for reply within second month	0.00
117 870	217 435	Extension for reply within third month	0.00
118 1,360	218 680	Extension for reply within fourth month	0.00
128 1,850	228 925	Extension for reply within fifth month	0.00
119 300	219 150	Notice of Appeal	0.00
120 300	220 150	Filing a brief in support of an appeal	0.00
121 260	221 130	Request for oral hearing	0.00
138 1,510	138 1,510	Petition to institute a public use proceeding	0.00
140 110	240 55	Petition to revive - unavoidable	0.00
141 1,210	241 605	Petition to revive - unintentional	0.00
142 1,210	242 605	Utility issue fee (or reissue)	0.00
143 430	243 215	Design issue fee	0.00
144 580	244 290	Plant issue fee	0.00
122 130	122 130	Petitions to the Commissioner	0.00
123 50	123 50	Petitions related to provisional applications	0.00
126 240	126 240	Submission of Information Disclosure Stmt	0.00
581 40	581 40	Recording each patent assignment per property (times number of properties)	40.00
146 760	246 380	Filing a submission after final rejection (37 CFR 1.129(a))	0.00
149 760	249 380	For each additional invention to be examined (37 CFR 1.129(b))	0.00
Other fee (specify) _____			0.00
Other fee (specify) _____			0.00
SUBTOTAL (3) (\$)			40.00

*Reduced by Basic Filing Fee Paid

SUBMITTED BY		Complete (if applicable)	
Typed or Printed Name	David G. Latwesen, Ph.D.	Reg. Number	38,533
Signature		Date	11/10/00
		Deposit Account User ID	

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.

PL 465688165

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

APPLICATION FOR LETTERS PATENT

* * * * *

**Phase Change Ink Formulation Containing a
Combination of a Urethane Resin, a Mixed
Urethane/Urearesin, a Mono-Amide and a
Polyethylene Wax**

* * * * *

INVENTORS

**Donald R. Titterington
Jeffrey H. Banning**

ATTORNEY'S DOCKET NO. D/A0306II

EL465688165

PHASE CHANGE INK FORMULATION CONTAINING A COMBINATION OF A URETHANE RESIN, A MIXED URETHANE/UREA RESIN, A MONO-AMIDE AND A POLYETHYLENE WAX

CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a continuation-in-part application, which is a continuation-in-part of U.S. Patent Application Serial No. 09/013,410, filed January 26, 1998; which is a continuation-in-part application of U.S. Patent Application Serial No. 08/672,815 filed on June 28, 1996, now U.S. patent No. 5,830,942. This application is also a continuation in part of U.S. Patent 5 Application Serial No. 09/078,190, filed May 13, 1998, which is a continuation-in-part application of U.S. Patent Application Serial No. 08/672,816 filed on June 28, 1996.

BACKGROUND

FIELD OF THE INVENTION

The present invention relates generally to phase change inks. Still further, the present invention relates to processes of using phase change inks in printing devices. Additionally, the present invention relates to processes of using polyethylene wax as a transparent overcoat layer on a printed substrate to provide improved document feed capability from photocopiers.

15 **DESCRIPTION OF THE RELEVANT ART**

In general, phase change inks (sometimes referred to as "hot melt inks") are in the solid phase at ambient temperature, but exist in the liquid phase at the elevated operating temperature of an ink jet printing device. At the jet operating temperature, droplets of liquid ink are ejected from the printing device and, when the ink droplets contact the surface of the printing media, 20 they quickly solidify to form a predetermined pattern of solidified ink drops. Phase change inks have also been investigated for use in other printing technologies such as gravure printing as referenced in U.S. Patent No. 5,496,879 and German patent publications DE 4205636AL and DE 4205713AL assigned to Siegwerk Farbenfabrik Keller, Dr. Rung and Co.

Phase change inks for color printing generally comprise a phase change ink carrier 25 composition, which is combined with a phase change ink compatible colorant. Preferably, a

colored phase change ink will be formed by combining the above-described ink carrier composition with compatible subtractive primary colorants. The subtractive primary colored phase change inks can comprise four component dyes, namely, cyan, magenta, yellow and black. U.S. Patent Nos. 4,889,506; 4,889,761; and 5,372,852 teach that the subtractive primary
5 colorants employed typically may comprise dyes from the classes of Color Index (C.I.) Solvent Dyes, Disperse Dyes, modified Acid and Direct Dyes, and a limited number of Basic Dyes. The colorants can also include pigments as exemplified in U.S. Patent No. 5,221,335, assigned to Coates Electrographics LTD. U.S. Patent Application Serial No. 08/381,610, filed January 30,
10 1995, and assigned to Tektronix, Inc. (now U.S. Patent No. 5,621,022), is directed to the use of a specific class of polymeric dyes in phase change ink compositions.

Phase change inks are desirable for ink jet printers since they remain in a solid phase at room temperature during shipping, long-term storage, and the like. Also, the problems associated with nozzle clogging due to ink evaporation are largely eliminated, thereby improving the reliability of ink jet printing. Furthermore, ink droplets can be applied directly onto a printing medium (substrate) and be configured to solidify immediately upon contact with the substrate. Migration of ink along the printing medium can thus be prevented and dot quality improved.

In addition to the above-referenced U.S. patents, many other patents describe materials for use in phase change ink jet inks. Some representative examples include U.S. Patent Nos. 3,653,932; 4,390,369; 4,484,948; 4,684,956; 4,851,045; 4,889,560; 5,006,170; and 5,151,120; as well as EP Application Nos. 0187352 and 0206286. These materials can include paraffins, microcrystalline waxes, polyethylene waxes, ester waxes, fatty acids and other waxy materials, fatty amide-containing materials, sulfonamide materials, resinous materials made from different natural sources (tall oil rosins and rosin esters are an example) and many synthetic resins, oligomers, polymers and co-polymers.
25

Separately, PCT Patent Application WO 94/14902, which was published on July 7, 1994 and is assigned to Coates Brothers PLC, teaches a hot melt ink containing a colorant and, as a vehicle for the hot melt ink, an oligourethane having a melting point of at least 65°C and obtained by reacting an aliphatic or aromatic diisocyanate with at least a stoichiometric amount of either: (i) a monohydric alcohol component; or (ii) a monohydric alcohol component followed by another different monohydric alcohol component; or (iii) a monohydric alcohol component, followed by a dihydric alcohol component, followed by a monohydric alcohol component.
30

This PCT patent application defines the monohydric alcohol component as either a monohydric aliphatic alcohol (e.g. C₁ to C₂₂ alcohols), an etherified dihydric aliphatic alcohol (e.g. propylene glycol methyl ether (PGME), dipropylene glycol methyl ether (DPGME), ethylene glycol butyl ether (EGBE), diethylene glycol butyl ether (DPGBE), tripropylene glycol butyl ether (TPGBE) and propylene glycol phenyl ether (PPL)); esterified dihydric aliphatic alcohol (e.g. the esterifying acid may be an ethylenically unsaturated acid (such as acrylic acid or methacrylic acid), thereby introducing ethylenic unsaturation into the oligourethane and rendering it suitable for eventual further additional polymerization (curing) after having been applied to a substrate by hot melt printing), or dihydric polyalkylene glycol. This PCT Application further defines the dihydric alcohol component as a dihydric aliphatic alcohol or a dihydric polyalkylene glycol (e.g. ethylene glycol, polyethylene glycol (PEG 1500), polypropylene glycol (PPG 750, 1000 and 1500), trimethylene glycol, dipropylene glycol, methylpropanediol and 1,6-hexanediol).

Also, PCT Patent Application WO 94/04619, assigned to the General Electric Company, teaches the use of ionomer materials in combination with image forming agents to form a hot melt ink jet ink. The ionomer materials can include many different types of copolymeric or polymeric ionomers, including carboxyl-functional polyurethanes prepared from a diol or polyol and a hydroxyl acid. Many other carrier materials and colorants for the image forming agent of the invention are included in this PCT application.

Furthermore, U.S. Patent Application Serial No. 08/672,815, (now U.S. Patent No. 5,830,815) assigned to the Assignee of the present invention, teaches phase change carrier compositions that comprise the combination of a urethane resin with a urethane/urea resin that may optionally contain other ingredients such as mono-amides and polyethylene waxes.

However, there is still a need for new materials for novel and different applications of phase change carrier compositions and inks containing such carrier compositions. There is also a need for low viscosity phase change carrier compositions and inks having non-polymeric resins and waxes designed for phase change ink jet and other forms of phase change ink printing. Such carrier compositions and inks being substantially transparent and having a reduced surface coefficient of friction as compared to presently known carrier compositions and inks. It would be advantageous if ink sticks which have an improved surface appearance and better release from molds and waste collection trays than previously known ink sticks could also be formed from such carrier compositions and inks. Additionally, it would be desirable if such phase change ink

and carrier compositions include improved blocking performance of finished prints than has been previously known.

BRIEF DESCRIPTION OF THE FIGURE

5 The figure is a schematic diagram of a chemical reaction utilized in particular aspects of the present invention.

SUMMARY

10 Embodiments in accordance with the present invention are directed to phase change carrier compositions comprising an admixture of (1) at least one urethane resin; and/or (2) at least one mixed urethane/urea resin; and/or (3) at least one mono-amide; and/or (4) at least one polyethylene wax.

15 Embodiments of the present invention are also directed to phase change ink compositions comprising the admixture of (a) the above-noted phase change carrier composition with (b) a phase change ink compatible colorant.

20 Embodiments of the present invention include methods for producing a layer of a phase change colored ink on the surface of a substrate by either direct or indirect printing wherein the phase change ink composition in the solid phase comprises an admixture of (a) the above-noted phase change carrier composition and (b) a phase change ink compatible colorant.

25 Other embodiments in accordance with the present invention encompass methods for using a polyethylene wax as an overcoat layer above a phase change ink layer on a printed substrate such as a sheet of paper.

Features of embodiments of the present invention directed to phase change carrier compositions, include a low viscosity, being substantially transparent and having a reduced surface coefficient of friction.

30 Features of embodiments in accordance with the present invention directed to phase change inks include ink sticks which have an improved surface appearance and better release from molds and waste collection trays than previously known ink sticks. Additional features of such phase change ink embodiments also include improved blocking performance of finished prints than has been previously known.

Advantageously, embodiments in accordance with the present invention encompassing

phase change carrier compositions can be design engineered to obtain desired properties for specific printing platforms and architectures.

In addition, embodiments of the present invention that include phase change inks are resins or waxes which are very pure and that are essentially free of salts and other insoluble 5 contaminants generally found in previously known phase change inks.

DETAILED DESCRIPTION

The term "nucleophile" in the present specification and claims is used as defined on page 179 of "Advanced Organic Chemistry", 3rd Edition by Jerry March, 81985 by John Wiley and 10 Sons, to describe a reagent that brings an electron pair to a reaction to form a new bond. The preferred nucleophiles of this invention are alcohols or amines, but it is understood that other nucleophilic functional groups that are capable of reacting with the isocyanate moiety could also be used in the invention.

The term "oligomer" in the current specification and claims is used as defined on page 15 7 of "Polymer Chemistry - The Basic Concepts" by Paul Hiemenz, 81984 by Marcel Dekker, Inc., to describe a term coined to designate molecules for which n (representing the number of repeating monomer units) is less than 10.

The term "isocyanate-derived resin" as used in the present specification and claims is defined as any monomeric, oligomeric or non-polymeric resinous material derived from the 20 reaction of mono-, di-, or poly-isocyanates with suitable nucleophilic molecules.

The terms "isocyanate-derived wax" as used in the present specification and claims is defined as any crystalline or semicrystalline waxy material derived from the reaction of a fatty isocyanate with a suitable nucleophile, or the reaction of a fatty nucleophile with a suitable isocyanate, or the reaction of a fatty nucleophile with a fatty isocyanate.

The term "urethane resin" or "urethane isocyanate-derived resin" as used in the present 25 specification and claims is defined as any resin that is a urethane which is the product of the reaction of an isocyanate and an alcohol.

The term "mixed urethane/urea resin" or "urethane/urea isocyanate-derived resin" as used in the present specification and claims is defined as any resin that is a mixed urethane/urea which 30 is the product of the reaction of an isocyanate, an alcohol and an amine.

Any suitable reaction condition for making urethane resins or mixed urethane/urea resins by condensing alcohols and/or amines with isocyanates can be employed in the practice of the

present invention. Generally, the reaction is carried out at elevated temperatures (e.g. about 60 °C to about 160 °C) in the presence of a urethane reaction catalyst such as dibutyltindilaurate, bismuth tris-neodecanoate, cobalt benzoate, lithium acetate, stannous octoate or triethylamine. The reaction conditions are typically an inert atmosphere, such as argon or nitrogen gas or other suitable atmosphere, to prevent oxidizing or yellowing the reaction products and to prevent undesirable side reactions. The mole ratio of reactants is adjusted so that the isocyanate functionalities are completely consumed in the reaction with a slight molar excess of alcohol or amine typically remaining. Conceptually the reactants can be added together in any order and/or added to the reaction as physical mixtures. However, in some embodiments in accordance with the present invention, reaction conditions and the order of the addition of reactants are controlled. First, reaction conditions and reactant additions are selected to provide a controlled exothermic reaction. Secondly, when reacting mixtures of alcohols and/or amines with diisocyanates such as isophorone diisocyanate (IPDI), the order of addition of the isocyanate and the different nucleophiles to the reaction is chosen to tailor the distribution of diurethane molecules, and/or mixed urethane/urea molecules, and/or diurea molecules in the final resin. When doing this, the different reactivities to isocyanates of alcohols versus amines are employed, as are the different reactivities of the two separate isocyanate groups on IPDI. See J.H. Saunders and K.C. Frisch's "Polyurethanes Part I, Chemistry" published by Interscience of New York, New York in 1962 and Olin Chemicals' Luxate™ IM isophorone diisocyanate technical product information sheet which provide further explanation of this chemistry. This control of the reaction conditions and order of addition of the reactants is done to specifically tailor or customize the different types of molecular species in the finished resin so that the resin will:

- (1) have a controlled viscosity that is designed for a specific application,
- (2) have a controlled glass transition temperature and/or melting point, and
- (3) have consistent properties from batch to batch.

The isocyanate-derived resins from these reactions are generally transparent solids having melting points in the range of about 20 °C to about 150 °C, viscosities in the range of about 10 cPs to about 5000 cPs at 150 °C and T_g's (glass transition point) of about -30 °C to about 100 °C. The isocyanate-derived waxes from these reactions are generally opaque waxy solids having sharp melting points from about 50 °C to about 130 °C, and viscosities of about 1 cPs to about 25 cPs at 140 °C. Such resins and waxes display properties such that the higher the T_g and the melting point, the higher the viscosity. While the structural activity relationships are not fully

understood, it is known that the T_g of isocyanate-derived resins is controlled by the proper choice of the mixture of nucleophiles in the reaction as illustrated in Table 3 in the aforementioned U.S. Application Serial No. 08/672,815 (now U.S. Patent No. 5,830,942). Varying one or more of the readily available commodity chemicals used as chemical precursors will permit custom-tailoring
5 of the properties of the isocyanate-derived resin and wax materials.

Alcohols employed in some embodiments of the present invention to react with difunctional and higher isocyanates to make either the urethane resins or the urethane/urea resins of this invention include monohydric alcohols. For instance, such monohydric alcohol encompass any aliphatic alcohol [e.g., a C₁-C₂₂ or higher linear alcohol, any branched alcohol or
10 any cyclic aliphatic alcohol such as methanol, ethanol, (n- and iso)-propanol, (n-, iso-, t-) butanol, (n-, iso-, t-, and the like) pentanol, (n-, iso-, t-, and the like) hexanol, (n-, iso-, t-, and the like) octanol, (n-, iso-, t-, and the like) nonanol, (n- and branched) decanols, (n- and branched) undecanols, (n- and branched) dodecanols, (n- and branched) hexadecanols, (n- and branched) octadecanols, 3-cyclohexyl-1-propanol, 2-cyclohexyl-1-ethanol, cyclohexylmethanol,
15 cyclohexanol, 4-methyl cyclohexanol, 4-ethylcyclohexanol, 4-t-butylcyclohexanol, and the like]; an aliphatic/aromatic alcohol [e.g., benzyl alcohol, octyl, nonyl, and dodecylphenol alkoxylates of octyl, nonyl, and dodecylphenol, and alkoxypheol]; aromatic alcohols such as phenol, naphthol, and the like, and their derivatives; fused ring alcohols (e.g., rosin alcohols, hydroabietyl alcohol, cholesterol, vitamin E, and the like). In some embodiments of the present
20 invention, other alcohols are employed and include N,N-dimethyl-N-ethanolamine, stearamide-monoethanolamine, tripropylene glycol monomethylether, hydroxybutanone, menthol, isoborneol, terpineol, 12-hydroxy steryl stearamide, and the like. In some embodiments, small amounts (on a molar basis) of polyols are incorporated into the reaction mixture to produce oligomeric species in the resins. Such polyols include, hydroabietyl alcohol, octylphenol ethoxylate and octadecyl alcohol.
25

Embodiments in accordance with the present invention employ amines to react with difunctional and higher isocyanates to make mixed urethane/urea resins. Such amines include any monofunctional amine, with the exception of any tertiary amine void of another nucleophilic functional group (e.g., triethylamine). Thus, mono-amines of some embodiments of the present
30 invention encompass aliphatic primary or secondary amines (e.g., a C₁-C₂₂ or higher linear amine, any branched amine or any cyclic aliphatic amine) such as methyl amine, ethyl amine, (n- and iso-)propyl amine, (n-, iso-, and t-) butyl amine, (n-, iso-, t-, and the like) pentyl amine,

(n-, iso-, t-, and the like) hexyl amine, (n-, iso-,t-, and the like) octyl amine, (n-, iso-, t-, and the like) nonyl amine, (n- and branched) decyl amine, (n- and branched) undecyl amines, (n- and branched) dodecyl amines, (n- and branched) hexadecyl amines, (n- and branched) dodecyl amines, dimethyl amine, diethyl amine, di(n- and iso-)propyl amines, di(n-, iso-, t-)butyl amine,
5 di(n-, iso-, t-, and the like)pentyl amine, di(n-, iso-, t-, and the like)hexyl amine, di(n-, iso-, t-, and the like)cyclohexyl amine, di(n-, iso-, t-, and the like)heptyl amine, di(n-, iso-, t-, and the like)octyl amine, di(n-, iso-, t-, and the like)decyl amine, di(n-, iso-, t-, and the like)dodecyl amine, di(n-, iso-, t-, and the like)octadecyl amine, cyclohexyl amine, 2,3-dimethyl-1-cyclohexylamine, piperidine, pyrrolidine, and the like. Such mono-amines also encompass aliphatic/aromatic amines (e.g., benzyl amine or analogues with longer or additional alkyl chains); aromatic amines such as aniline, anisidine, and the like; fused ring amines such as rosin amine, dehydroabietyl amine, dihydroabietyl amine, hydroabietyl amine, and the like; and miscellaneous amines (e.g., adamantyl amine, isonipecotamide, polyoxyalkylenmonoamines, such as M-series Jeffamines available commercially from Huntsman Chemical Company of Austin, Texas). ; 3,3'-diamino-N-methyl-dipropylamine, and the like. In addition, in embodiments where oligomeric species are formed, small amounts (on a molar basis) of polyamines are incorporated into the reaction mixture. A suitable amine is octadecyl amine.

Alcohols for reacting with monofunctional isocyanates to make the mixed urethane/urea resins in accordance with some embodiments of this invention include any monohydric alcohol. For instance, such monohydric alcohols are any aliphatic alcohol [e.g., a C₁-C₂₂ or higher linear alcohol, any branched alcohol or any cyclic aliphatic alcohol such as methanol, ethanol, (n- and iso-)propanol, (n-, iso-, and t-) butanol, (n-, iso-, t-, and the like) pentanol, (n-, iso-, t-, and the like) hexanol, (n-, iso-, t-, and the like) octanol, (n-, iso-, t-, and the like) nonanol, (n- and branched) decanols, (n- and branched) undecanols, (n- and branched) dodecanols, (n- and branched) hexadecanols, (n- and branched) octadecanols, 3-cyclohexyl-1-propanol, 2-cyclohexyl-1-ethanol, cyclohexylmethanol, cyclohexanol, 4-methyl cyclohexanol, 4-ethylcyclohexanol, 4-t-butylcyclohexanol, and the like]; an aliphatic/aromatic alcohol (e.g., benzyl alcohol, octyl, nonyl, and dodecylphenol alkoxylates or octyl, nonyl, and dodecylphenol, alkoxyphenol); aromatic alcohols such as phenol, naphthol, and the like, and their derivatives; fused ring alcohols (e.g., rosin alcohols, hydroabietyl alcohol, cholesterol, vitamin E, and the like). Other suitable alcohols include N,N-dimethyl-N-ethanolamine, stearamide-monoethanolamine, tripropylene glycol monomethylether, hydroxybutanone, menthol, isoborneol, terpineol, 12-hydroxy stearyl
20
25
30

stearamide, and the like. Further, multifunctional alcohols can be utilized in some embodiments of the present invention. Exemplary multifunctional alcohols are ethylene glycol, diethylene glycol, triethylene glycol, dimethylolepropionic acid, sucrose, polytetramethylene glycol (MW <~3000), polypropylene glycol (MW <~3000), polyester polyols (MW <~3000), polyethylene glycol (MW <~3000), pentaerythritol, triethanol amine, glycerin, 1,6-hexanediol, N-methyl-N,N-diethanol amine, trimethylol propane, N,N,N',N'-tetrakis(2-hydroxypropyl)ethylenediamine, and the like. In some embodiments in accordance with the present invention, octadecanol is employed.

Some embodiments of the present invention encompass amines for reacting with monofunctional isocyanates to make isocyanate-derived waxes and resins. Such amines include monofunctional amines, with the exception of tertiary amines void of another nucleophilic functional groups (e.g., triethylamine). For instance, the monoamine could be any aliphatic primary or secondary amine [e.g., a C₁-C₂₂ or higher linear amine, any branched amine or any cyclic aliphatic amine such as methyl amine, ethyl amine, (n- and iso-)propyl amine, (n-, iso-, and t-) butyl amine, (n-, iso-, t-, and the like) pentyl amine, (n-, iso-, t-, and the like) hexyl amine, (n-, iso-, t-, and the like) octyl amine, (n-, iso-, t-, and the like) nonyl amine, (n- and branched) decyl amine, (n- and branched) undecyl amine, (n- and branched) octadecyl amine, (n- and branched) hexadecyl amine, (n- and branched) dodecyl amine, dimethyl amine, diethyl amine, di(n-, and iso-)propyl amine, di(n-, iso-, t-)butyl amine, di(n-, iso-, t-, and the like)pentyl amine, di(n-, iso-, t-, and the like)hexyl amine, di(n-, iso-, t-, and the like)cyclohexyl amine, di(n-, iso-, t-, and the like)heptyl amine, di(n-, iso-, t-, and the like)octyl amine, di(n-, iso-, t-, and the like)decyl amine, di(n-, iso-, t-, and the like)octadecyl amine, di(n-, iso-, t-, and the like)dodecyl amine, cyclohexyl amine, 2,3-dimethyl-1-cyclohexylamine, piperidine, pyrrolidine, and the like]; any aliphatic/aromatic amines (e.g., benzyl amine or analogues with longer or additional alkyl chains); aromatic amines such as aniline, anisidine, and the like; fused ring amines such as rosin amine, dehydroabietyl amine, dihydroabietyl amine, hydroabietyl amine, and the like. Also, miscellaneous amines (e.g., adamantyl amine, isonipecotamide, polyoxyalkylenemono-, di-, or triamines, such as M-, D-, and T-series Jeffamines available commercially from Huntsman Chemical Company of Austin, Texas); 3,3'-diamino-N-methyl-dipropylamine, and the like can be utilized, as well as multifunctional amines such as polyethylene imine; ethylene diamine; hexamethylene diamine; isomers of cyclohexyldiamines; 1,3-pentadiamine; 1,12-dodecanediamine; 3-dimethylamino-propylamine; 4,7,10-trioxa-1,13-tridecanediamine;

diethylene triamine; 3,3-diamino-N-methyldipropylamine; tris(2-aminoethyl)amine, and the like. A preferred amine can be octadecylamine.

Additionally, hydroxyl/amino containing compounds can be employed (with di- and higher functionality isocyanates taking advantage of the difference in reactivity of the amine over the hydroxyl group, or with monoisocyanates reacting with the amine preferentially or with both the amine and the hydroxyl groups). Examples of this include ethanolamine, diethanolamine, and the like.

Additionally, amides or other nucleophile containing compounds can be reacted with the isocyanates (mono, di, and the like). Some examples include: urea, oleamide, stearamide, or the like.

Preferred precursors to the urethane resins and urethane/urea resins of the present invention include mono-, di- and other poly-isocyanates. Examples of monoisocyanates include octadecylisocyanate; octylisocyanate; butyl and t-butylisocyanate; cyclohexyl isocyanate; adamantyl isocyanate; ethylisocyanatoacetate; ethoxycarbonylisocyanate; phenyliso-cyanate; alphamethylbenzyl isocyanate; 2-phenylcyclopropyl isocyanate; benzylisocyanate; 2-ethylphenylisocyanate; benzoylisocyanate; meta and para-tolylisocyanate; 2-, 3-, or 4-nitrophenylisocyanates; 2-ethoxyphenyl isocyanate; 3-methoxyphenyl isocyanate; 4-methoxyphenylisocyanate; ethyl 4-isocyanatobenzoate; 2,6-dimethylphenylisocyanate; 1-naphthylisocyanate; (naphthyl)ethylisocyanates; and the like. Examples of diisocyanates include isophorone diisocyanate (IPDI); toluene diisocyanate (TDI); diphenylmethane-4,4'-diisocyanate (MDI); hydrogenated diphenylmethane-4,4'-diisocyanate (H_{12} MDI); tetra-methyl xylene diisocyanate (TMXDI); hexamethylene-1,6-diisocyanate (HDI); hexamethylene-1,6-diisocyanate; naphtylene-1,5-diisocyanate; 3,3'-dimethoxy-4,4'-biphenyldiisocyanate; 3,3'-dimethyl-4,4'-bimethyl-4,4'-biphenyldiisocyanate; phenylene diisocyanate; 4,4'-biphenyldiisocyanate; trimethylhexamethylene diisocyanate; tetramethylene xylene diisocyanate; 4,4'-methylenebis(2,6-diethylphenyl isocyanate); 1,12-diisocyanatododecane; 1,5-diisocyanato-2-methylpentane; 1,4-diisocyanatobutane; and cyclohexylene diisocyanate and its isomers; uretidione dimers of HDI; and the like. Examples of triisocyanates or their equivalents include the trimethylolpropane trimer of TDI, and the like, isocyanurate trimers of TDI, HDI, IPDI, and the like, and biuret trimers of TDI, HDI, IPDI, and the like. Examples of higher isocyanate functionalities include copolymers of TDI/HDI, and the like, as well as MDI oligomers.

Phase change inks of this invention can contain a phase change carrier system or

00000000000000000000000000000000

composition. The phase change carrier composition is generally designed for use in either a direct printing mode or use in an indirect or offset printing transfer system. In the direct printing mode, the phase change carrier composition is generally made up of one or more chemicals that provide properties to allow the phase change ink (1) to be applied in a thin film of uniform thickness on the final receiving substrate when cooled to the ambient temperature after printing directly to the substrate; (2) to be ductile while retaining sufficient flexibility so that the applied image on the substrate will not fracture upon bending; and (3) to possess a high degree of lightness, chroma, transparency and thermal stability. In an offset printing transfer or indirect printing mode, the phase change carrier composition is designed to possess not only the above mentioned properties, but certain fluidic and mechanical properties, as described in U.S. Patent No. 5,389,958. Exemplary phase change carrier composition and the inks made therefrom comprised by the current invention contain urethane resins, or urethane/urea resins. The carrier compositions can be supplemented with (one or more) additional ingredients to prepare commercial phase change carrier compositions. The urethane resins, and mixed urethane/urea resin materials of the current invention can be tailored to have the desirable properties mentioned above when used in the carrier composition of the inks of the present invention by varying one or more of the readily available commodity chemical precursors.

The phase change carrier compositions of the current invention may be used in combination with conventional phase change ink colorant materials such as Color Index (C.I.) Solvent Dyes, Disperse Dyes, modified Acid and Direct Dyes, Basic Dyes, Sulphur Dyes, Vat Dyes, and/or polymeric dyes such as those disclosed in U.S. Patent Application Serial No. 08/381,610 (now U.S. Patent No. 5,621,022), and/or pigments to produce a phase change ink. Alternatively, the phase change carrier compositions of the current invention may employ colored urethane resins or urethane/urea resins or other isocyanate-derived colored resins as described in U.S. patent application Serial No. 08/672,617, filed June 28, 1996 and assigned to the assignee of the present invention (now U.S. Patent No. 5,780,528), to produce a phase change ink.

Phase change carrier compositions of the present invention can comprise a mono-amide. A mono-amide compound typically comprises either a primary or secondary mono-amide, but is preferably a secondary mono-amide. Of the primary mono-amides, stearamide, such as KEMAMIDE S, manufactured by Witco Chemical Company, can be employed herein. As for the secondary mono-amides, behenyl benenamide (KEMAMIDE EX-666), and stearyl

stearamide (KEMAMIDE S-180), both manufactured by Witco Chemical Company, are extremely useful mono-amides. However, stearyl stearamide (KEMAMIDE S-180) is the mono-amide of choice in producing the phase change ink compositions of the present invention.

Phase change carrier compositions of the present invention can comprise at least one polyethylene wax. Preferably, the polyethylene wax has a molecular weight of about 500 to about 5,000; more preferably, of about 550 to about 2,000; and, most preferably, of about 500 to 1,000. Suitable polyethylene waxes are Polywax 655, Polywax 850, or Polywax 1000, all available from Petrolite.

Preferably, the total amount of urethane resin or resins in the phase change carrier composition and the inks made therefrom will comprise about 10% to about 40%, more preferably, about 15-35% and most preferably, about 20-30%, by weight of the carrier composition. Preferably, the total amount of mixed urethane/urea resin or resins in the phase change carrier composition will likewise comprise about 10% to about 40%, more preferably about 15-35% and most preferably, about 20-30%, by weight of the carrier composition. Preferably, the total amount of mono-amide wax and polyethylene wax combined will comprise about 40% to about 70%, more preferably, about 45-60% and most preferably about 48-57% by weight of the carrier composition.

The ratio of mono-amide wax to the polyethylene wax is preferably from about 200:1 to 9:1, by weight. More preferably, this ratio is from about 50:1 to about 12:1, by weight and, most preferably, about 25:1 to about 16:1, by weight.

Prior art phase change inks for use in direct and indirect transfer printing systems are described in U.S. Patent Nos. 4,889,560 and 5,372,852. These inks consist of a phase change ink carrier composition comprising one or more fatty amide-containing materials, usually consisting of a mono-amide wax and a tetra-amide resin, one or more tackifiers, one or more plasticizers and one or more antioxidants, in combination with compatible colorants. A preferred tetra-amide resin is a dimer acid based tetra-amide that is the reaction product of dimer acid, ethylene diamine, and stearic acid. The typical mono-amide is stearyl stearamide. A preferred tackifier resin is a glycerol ester of hydrogenated abietic (rosin) acid and a preferred antioxidant is that provided by Uniroyal Chemical Company under the tradename Naugard 524. The urethane and urethane/urea resins employed in this invention can replace one or more of the ingredients in this prior art carrier composition or inks employing the resin components of the present invention can have all of these prior art ingredients replaced by the urethane and/or

urethane/urea resins disclosed herein and/or by isocyanated derived waxes.

Among the advantages of inks formulated in accordance with the present invention relative to prior art phase change inks are:

(1) The urethane resins and mixed urethane/urea resins of this invention are very pure, being free of salts and other insoluble contaminants. This makes the inks made from these materials easy to filter and provides for high reliability in ink jet printing devices. This can be a major advantage.

(2) The urethane resins and mixed urethane/urea resins of this invention may be specifically tailored to give certain physical properties that optimize the performance of the inks of this invention in ink jet printing devices and on the output substrate. These desirable ink properties include melting point, viscosity, transparency and the dynamic mechanical properties referenced in the aforementioned U.S. Patent No. 5,389,958.

(3) The urethane resins and mixed urethane/urea resins of this invention are used in combination with the mono-amide wax and polyethylene wax to give ink compositions that display an improved yield stress versus temperature curve over prior art ink compositions. This enables ink droplets to be spread and fused at elevated temperatures during the fusing and transfer steps in an indirect printing process, but at a lower pressure than was possible with prior art inks.

(4) The ink formulations with the added polyethylene wax disclosed herein exhibit better surface finishes in the final poured, molded and hardened ink sticks when compared to equivalent ink sticks formulated without the polyethylene wax, as well as exhibiting better release characteristics from their plastic molds. The waste ink resulting from ink sticks of the present invention also releases more easily from the waste ink trays in the printers for which they are intended for use. Finally, prints made from inks with the polyethylene wax additive also exhibit better blocking resistance at elevated temperatures.

Many other patents describe other materials for use in phase change ink jet inks. Some representative examples include U.S. Patent Nos. 3,653,932; 4,390,369; 4,484,948; 4,684,956; 4,851,045; 5,006,170; 5,151,120; EP Application Nos. 0187352 and 0206286; and PCT Patent Application WO 94/04619. These other materials can include paraffins, microcrystalline waxes, ester waxes, amide waxes, fatty acids, fatty alcohols, fatty amides and other waxy materials, sulfonamide materials, resinous materials made from different natural sources (tall oil rosins and rosin esters are an example) and many synthetic resins, oligomers, polymers, co-polymers, and

ionomers. It will be obvious to those skilled in the art that the phase change carrier composition of this invention could optionally contain any of the optional other materials.

The aforementioned U.S. Patent No. 5,496,879 and German patent publications DE 4205636AL and DE 4205713AL, assigned to Siegwerk Farbenfabrik Keller, Dr. Rung and Co., 5 describe materials used for phase change or hot melt gravure printing. It will be obvious to those skilled in the art that the isocyanate-derived materials of this current invention would be compatible with those materials and could also be used in that application or other similar printing methods that employ hot melt ink technology.

It also will be obvious to those skilled in the art that other ink colors besides the 10 subtractive primary colors are desirable for applications, such as postal marking or industrial marking and labeling using phase change printing, and that this invention is applicable to these needs. Infrared (IR) or ultraviolet (UV) absorbing dyes can also be incorporated into the inks of this invention for use in applications such as "invisible" coding or marking of products.

The inks of the present invention can be equally well employed in apparatus for direct 15 or indirect (offset) printing applications. When employed in direct printing applications a suitable method of printing or producing a layer of a phase change colored ink directly on the surface of a substrate can comprise:

- (1) forming a phase change ink composition in the solid phase, comprising an admixture of (a) a phase change carrier composition containing at least one isocyanate-derived resin or wax and (b) a phase change compatible colorant.
- (2) transferring the solid phase, phase change colored ink composition to a phase change ink application means or print head;
- (3) raising the operating temperature of the application means or print head to a level whereby a liquid phase, phase change colored ink composition is formed;
- (4) providing a substrate in proximity to the application means;
- (5) applying a predetermined pattern of the liquid phase, phase change colored ink composition to at least one surface of the substrate; and
- (6) lowering the temperature of the applied ink composition to form a solid phase, phase change ink pattern on the substrate.

30 An appropriate direct printing process is described in greater detail in U.S. Patent No. 5,195,430.

When employed in indirect or offset printing applications a suitable method of printing or producing a layer of a phase change colored ink indirectly on the surface of a substrate by transferring from an intermediate transfer surface can comprise:

- (1) forming a phase change ink composition in the solid phase, comprising an admixture of (a) a phase change carrier composition containing at least one isocyanate-derived resin or wax and (b) a phase change compatible colorant.
- (2) transferring the solid phase, phase change colored ink composition to a phase change ink application means or a print head;
- (3) raising the operating temperature of the application means or print head to a level whereby a liquid phase, phase change colored ink composition is formed;
- (4) providing an intermediate transfer surface in proximity to the application means;
- (5) applying a predetermined pattern of the liquid phase, phase change colored ink composition to the intermediate transfer surface;
- (6) lowering the temperature of the applied ink composition to form a solid phase, phase change ink pattern on the intermediate transfer surface at a second, intermediate temperature;
- (7) transferring said phase change ink composition from the intermediate transfer surface to a final substrate; and
- (8) fixing the phase change ink composition to the substrate to form a printed substrate, the phase change ink composition having (a) a compressive yield strength which will allow it to be malleable to spread and deform without an increase in stress when compressive forces are applied thereto at the second operating temperature, and sufficient internal cohesive strength to avoid shear banding and weak behavior when said phase change ink composition is transferred and fixed to said substrate, and (b) a ductility on the substrate after fixing.

An appropriate offset or indirect printing process is described in greater detail in U.S. Patent No. 5,389,958.

The polyethylene wax of this invention can also be employed as an overcoat layer on a printed substrate. In this application, a substrate, preferably paper, is printed with any ink, preferably with a phase change ink, more preferably with a phase change ink composition of the present invention. The printed substrate is then coated with the polyethylene wax described

09654735096500

above. Preferably, this overcoat only coats a minority portion of the surface area of the printed substrate, more preferably a regularly spaced dot matrix covering from about 1% to about 25% of the surface area of the printed substrate.


In one example of using an overcoat, printed pages of paper are made on a Tektronix Phaser™ 340 ink jet ink printer by conventional means. The thus-produced printed paper then has a matrix of polyethylene wax dots (with about a 1% to about 5% fill) printed over the image. This wax dot matrix can be printed with another or the same ink jet printer. Preferably, the substrate after this overcoat operation is passed through a set of pressure rollers in the same ink jet printer to embed the polyethylene wax into the surface of the printed substrate. This treatment gives enhanced antiblocking properties to the prints (less transfer of ink from page to paper lying on top of output page when weighted and left standing) and also enables the prints to be fed through a copier automatic document feed (ADF) because of the decreased stickiness of the ink. Alternatively, the polyethylene wax could be applied to finished prints by other means such as an anilox roller, or could be jetted onto the transfix drum in an appropriate dot or other matrix before the rest of the image is applied to that drum, thus leaving the dot matrix of wax on top of the image after the transfix process.

The present invention is further described in detail by means of the following Examples and Comparisons. All parts and percentages are by weight and all temperatures are degrees Celsius unless explicitly stated otherwise. It is to be noted that while the following examples may recite only one colorant, it is to be understood that each individual example is only illustrative and any of the primary colorants (cyan, yellow, magenta and black) used in subtractive color printing could be employed in each instance.

A particular embodiment of the present invention is described with reference to the Figure as a method of forming a urethane material. Specifically, ABITOL E™ (available from Hercules) is utilized as a starting reagent. ABITOL E is shown by a representative structure, and comprises hydroabietyl alcohol (CAS[133-93-6]), methyl ester of hydrogenated rosin (CAS[8050-15-5]), and decarboxylated rosin (CAS[8050-18-8]). The ABITOL E is reacted with isophorone diisocyanate (CAS[4098-71-91]) to form a urethane product. Typically, dibutyltindilaurate (CAS[77-58-7]) is provided as a catalyst (and is provided to a concentration of less than 1% by weight relative to other reactants). The relative amount of isophorone diisocyanate to ABITOL E is preferably such that the isophorone diisocyanate is a limiting reagent in the reaction.

ABITOL E is an exemplary alcohol reagent. Such exemplary reagent is a member of a class of monohydric alcohols comprising fused rings. The fused rings may or may not comprise double bonds. The exemplary reagent is also a member of a class of alcohols comprising at least three fused rings.

5 The urethane product is a member of a class of materials that can be represented by formula 1.



10 The groups R₁-R₁₉ of formula 1 each comprise, independently of the others, a hydrogen atom, an alkyl group (either substituted or unsubstituted), which can be linear, branched, unsaturated, and/or cyclic, typically with from about 1 to about 100 carbon atoms, preferably with from about 12 to about 60 carbon atoms, and more preferably with from about 18 to about 50 carbon atoms, although the number of carbon atoms can be outside of these ranges, an aryl group (either substituted or unsubstituted), typically with from about 6 to about 24 carbon atoms, preferably


09654726 090500

with from about 6 to about 14 carbon atoms, and more preferably with from about 6 to about 10 carbon atoms, although the number of carbon atoms can be outside of these ranges, an arylalkyl group or alkylaryl group (either substituted or unsubstituted), typically with from about 7 to about 100 carbon atoms, preferably with from about 10 to about 60 carbon atoms, and more preferably with from about 18 to about 50 carbon atoms, although the number of carbon atoms can be outside of these ranges, a heterocyclic group (either substituted or unsubstituted), typically with from about 3 to about 50 carbon atoms, preferably with from about 3 to about 18 carbon atoms, and more preferably with from about 3 to about 12 carbon atoms, although the number of carbon atoms can be outside of these ranges, wherein the hetero atom or atoms can be, but are not limited to, atoms such as oxygen, nitrogen, sulfur, phosphorus, silicon, and the like, as well as mixtures thereof, wherein two or more of the R groups can be joined together to form a ring, and where the substituents on the substituted alkyl, aryl, arylalkyl, alkylaryl, and heterocyclic groups can be (but are not limited to) hydroxy groups, amine groups, imine groups, ammonium groups, pyridine groups, pyridinium groups, ether groups, aldehyde groups, ketone groups, ester groups, amide groups, carboxylic acid groups, carbonyl groups, thiocarbonyl groups, sulfate groups, sulfonate groups, sulfide groups, sulfoxide groups, phosphine groups, phosphonium groups, phosphate groups, cyano groups, nitrile groups, mercapto groups, nitroso groups, halogen atoms, nitro groups, sulfone groups, acyl groups, acid anhydride groups, azide groups, mixtures thereof, and the like, wherein any two or more substituents can be joined together to form a ring.

Further one or more of groups R₁-R₁₉ can be comprised by a ring structure. The segment (CH₂)_X comprises one or more methylene groups.

A more specific description of a class encompassing the urethane product of the Figure is shown below as formula 2.

2.




10
The groups R₁-R₃₀ of formula 2 comprise, independently of the others, a hydrogen atom, an alkyl group (either substituted or unsubstituted), which can be linear, branched, unsaturated, and/or cyclic, typically with from about 1 to about 100 carbon atoms, preferably with from about 12 to about 60 carbon atoms, and more preferably with from about 18 to about 50 carbon atoms, although the number of carbon atoms can be outside of these ranges, an aryl group (either substituted or unsubstituted), typically with from about 6 to about 24 carbon atoms, preferably with from about 6 to about 14 carbon atoms, and more preferably with from about 6 to about 10

carbon atoms, although the number of carbon atoms can be outside of these ranges, an arylalkyl group or alkylaryl group (either substituted or unsubstituted), typically with from about 7 to about 100 carbon atoms, preferably with from about 10 to about 60 carbon atoms, and more preferably with from about 18 to about 50 carbon atoms, although the number of carbon atoms
5 can be outside of these ranges, a heterocyclic group (either substituted or unsubstituted), typically with from about 3 to about 50 carbon atoms, preferably with from about 3 to about 18 carbon atoms, and more preferably with from about 3 to about 12 carbon atoms, although the number of carbon atoms can be outside of these ranges, wherein the hetero atom or atoms can be, but are not limited to, atoms such as oxygen, nitrogen, sulfur, phosphorus, silicon, and the like, as well
10 as mixtures thereof, wherein two or more of the R groups can be joined together to form a ring, and where the substituents on the substituted alkyl, aryl, arylalkyl, alkylaryl, and heterocyclic groups can be (but are not limited to) hydroxy groups, amine groups, imine groups, ammonium groups, pyridine groups, pyridinium groups, ether groups, aldehyde groups, ketone groups, ester groups, amide groups, carboxylic acid groups, carbonyl groups, thiocarbonyl groups, sulfate groups, sulfonate groups, sulfide groups, sulfoxide groups, phosphine groups, phosphonium groups, phosphate groups, cyano groups, nitrile groups, mercapto groups, nitroso groups, halogen atoms, nitro groups, sulfone groups, acyl groups, acid anhydride groups, azide groups, mixtures thereof, and the like, wherein any two or more substituents can be joined together to form a ring.
15 The segments $(CH_2)_X$, $(CH_2)_Y$, and $(CH_2)_Z$ comprise one or more methylene groups and can be the same as one another or different from one another.

20

A yet more specific description of a class encompassing the urethane product of the Figure is shown below as formula 3.

3.



10
The groups R₁, R₂, R₃, R₄, R₅, R₆, R₇ and R₈ of formula 3 comprise, independently of the others, a hydrogen atom, an alkyl group (either substituted or unsubstituted), which can be linear, branched, unsaturated, and/or cyclic, typically with from about 1 to about 100 carbon atoms, preferably with from about 12 to about 60 carbon atoms, and more preferably with from about 18 to about 50 carbon atoms, although the number of carbon atoms can be outside of these ranges, an aryl group (either substituted or unsubstituted), typically with from about 6 to about 24 carbon atoms, preferably with from about 6 to about 14 carbon atoms, and more preferably with from about 6 to about 10 carbon atoms, although the number of carbon atoms can be outside

of these ranges, an arylalkyl group or alkylaryl group (either substituted or unsubstituted), typically with from about 7 to about 100 carbon atoms, preferably with from about 10 to about 60 carbon atoms, and more preferably with from about 18 to about 50 carbon atoms, although the number of carbon atoms can be outside of these ranges, a heterocyclic group (either substituted or unsubstituted), typically with from about 3 to about 50 carbon atoms, preferably with from about 3 to about 18 carbon atoms, and more preferably with from about 3 to about 12 carbon atoms, although the number of carbon atoms can be outside of these ranges, wherein the hetero atom or atoms can be, but are not limited to, atoms such as oxygen, nitrogen, sulfur, phosphorus, silicon, and the like, as well as mixtures thereof, wherein two or more of the R groups can be joined together to form a ring, and where the substituents on the substituted alkyl, aryl, arylalkyl, alkylaryl, and heterocyclic groups can be (but are not limited to) hydroxy groups, amine groups, imine groups, ammonium groups, pyridine groups, pyridinium groups, ether groups, aldehyde groups, ketone groups, ester groups, amide groups, carboxylic acid groups, carbonyl groups, thiocabonyl groups, sulfate groups, sulfonate groups, sulfide groups, sulfoxide groups, phosphine groups, phosphonium groups, phosphate groups, cyano groups, nitrile groups, mercapto groups, nitroso groups, halogen atoms, nitro groups, sulfone groups, acyl groups, acid anhydride groups, azide groups, mixtures thereof, and the like, wherein any two or more substituents can be joined together to form a ring. hydrogen, alkyl groups or aryl groups.

The urethane product of the Figure (or any members of the urethane products encompassed by formulas 1-3), can be incorporated into phase change inks. For instance, such urethane products can be combined with polyethylene waxes and/or mono-amide compounds to form phase change ink carrier compositions. Phase change inks comprising the urethane products can be printed by, for example, either the direct or offset printing methodologies described previously.

EXAMPLE 1

The Reaction Product of Octyphenol Ethoxylate, Isophorone
Diisocyanate and Yellow Reactive Colorant

5

About 525.0 grams (4.73 equiv.) of isophorone diisocyanate¹ and 1.5 grams of dibutyltindilaurate² catalyst, followed by 986 grams (3.88 equiv.) of octylphenol ethoxylate³, were added to a 3000 ml three-neck resin kettle equipped with a Trubore stirrer, N₂ atmosphere inlet, and a thermocouple-temperature controller. The reaction mixture was heated to about 10 135°C, about 346.1 grams (0.497 equiv.) of a yellow polymeric colorant corresponding to Colorant A from Table I of U.S. Patent No. 5,231,135 were added and the reaction mixture was heated for approximately 2 hours. An additional about 110.0 grams (0.433 equiv.) of octylphenol ethoxylate³ were added and the reaction mixture was heated at about 150°C for approximately 15 2 hours. An FT-IR of the product was obtained to insure all of the isocyanate (NCO) functionality was consumed. The absence (disappearance) of a peak at about 2285 cm⁻¹ (NCO) and the appearance (or increase in magnitude) of peaks at about 1740-1680 cm⁻¹ and about 1540-1530 cm⁻¹ corresponding to urethane frequencies were used to confirm this. The diurethane reaction product was poured into aluminum molds and allowed to cool and harden. This final colored resin product was characterized by the following physical properties: viscosity of about 20 121 cPs as measured by a Ferranti-Shirley cone-plate viscometer at about 140°C, a melting point of about 38°C to about 115°C as measured by electrothermal capillary melting point apparatus, a T_g of about 12.4°C as measured by differential scanning calorimetry using a DuPont 2100 calorimeter at a scan rate of 20°C/minute, and a spectral strength of about 5634 milliliters Absorbance Units per gram at λ max as measured by dilution in n-butanol using a Perkin Elmer 25 Lambda 2S UV/VIS spectrophotometer.

¹ Desmodur I B Isophorone diisocyanate available from Bayer Corp. of Pittsburg, Pennsylvania.

² Dibutyltindilaurate available from Aldrich Chemicals of Milwaukee, Wisconsin.

³ IGEPAL CA-210 octylphenol ethoxylate is available from Rhone-Poulenc Co., Cranbury, NJ.

EXAMPLE 2

The Reaction Product of 1.5 Parts Hydroabietyl Alcohol, 0.5 Parts Octadecyl Amine, and Isophorone Diisocyanate

5

About 240.2 grams (0.676 moles) of hydroabietyl alcohol⁴ was added to a 1000 ml four-neck resin kettle equipped with a Trubore stirrer, an N₂ atmosphere inlet, 200 ml addition funnel, and a thermocouple temperature controller. About 100.0 grams (0.45 moles) of isophorone diisocyanate⁵ was added to the addition funnel. Agitation of the hydroabietyl alcohol first was
10 begun and then all of the isophorone diisocyanate was added over approximately 5 minutes. About 0.22 grams of dibutyltindilaurate⁶ catalyst was added and the reaction mixture heated to about 125 °C under an N₂ atmosphere. After 4 hours at 125 °C, about 59.95 grams (0.225 moles)
15 of octadecyl amine⁷ was added and the temperature raised to about 150 °C and held for approximately 2 hours. An FT-IR of the reaction product was run to insure all of the NCO functionality was consumed. The absence (disappearance) of a peak at about 2285 cm⁻¹ (NCO) and the appearance (or increase in magnitude) of peaks at about 1705-1635 cm⁻¹ and about 1515-1555 cm⁻¹ corresponding to urea frequencies and about 1740-1680 cm⁻¹ and about 1540-1530 cm⁻¹ corresponding to urethane frequencies were used to confirm this. The final mixed urethane/urea
20 resin product was poured into aluminum molds and allowed to cool and harden. This final product was a clear solid resin at room temperature characterized by the following physical properties: viscosity of about 314.8 cPs as measured by a Ferranti-Shirley cone-plate viscometer at about 140 °C, a melting point of from about 67.9 °C to about 87.0 °C as measured by an electrothermal capillary melting point apparatus, and a T_g of about 23 °C as measured by differential scanning calorimetry using a DuPont 2100 calorimeter at a scan rate of 20 °C/minute.

25

⁴ Arbitol E B Hydroabietyl alcohol available from Hercules Inc. of Wilmington, Delaware.

⁵ Desmodur I B Isophorone diisocyanate available from Bayer Corp. of Pittsburgh, Pennsylvania.

⁶ Dibutyltindilaurate available from Aldrich Chemicals of Milwaukee, Wisconsin.

⁷ Octadecyl amine (technical grade) available from ACROS Organics of New Jersey.

EXAMPLE 3

The Reaction Product of Octyphenol Ethoxylate, Isophorone Diisocyanate and Cyan Reactive Colorant

5

About 525.0 grams (4.73 equiv.) of isophorone diisocyanate⁸, about 1.5 grams of dibutyltindilaurate⁹ catalyst, and about 992.0 grams (3.91 equiv.) of octylphenol ethoxylate¹⁰ were added to a 3000 ml three-neck resin kettle equipped with a Trubore stirrer, a N₂ atmosphere inlet, and a thermocouple-temperature controller. The reaction mixture was heated to about 10 135°C and held for approximately 3.5 hours with stirring under nitrogen. About 240.6 grams (0.473 equiv.) of a cyan polymeric colorant¹¹ were then added and the mixture was heated at about 150°C for approximately 2 hours. An FT-IR of the product was obtained to insure all of the isocyanate (NCO) functionality was consumed. The absence (disappearance) of a peak at about 15 2285 cm⁻¹ (NCO) and the appearance (or increase in magnitude) of peaks at about 1740-1680 cm⁻¹ and about 1540-1530 cm⁻¹ corresponding to urethane frequencies were used to confirm this. The diurethane reaction product was poured into aluminum molds and allowed to cool and harden. This final colored resin product was characterized by the following physical properties: viscosity of about 181.8 cPs as measured by a Ferranti-Shirley cone-plate viscometer at about 20 140°C, a melting point of about 59.9-70.2°C as measured by electrothermal capillary melting point apparatus, and a T_g of about 23.1°C as measured by differential scanning calorimetry using a DuPont 2100 calorimeter at a scan rate of 20°C/minute, and a spectral strength of about 5588 milliliters Absorbance Units per gram at λ max as measured by dilution in n-butanol using a Perking Elmer Lambda 2S UV/VIS spectrophotometer.

⁸ Desmodur I B Isophorone diisocyanate available from Bayer Corp. of Pittsburgh, Pennsylvania.

⁹ Dibutyltindilaurate available from Aldrich Chemicals of Milwaukee, Wisconsin.

¹⁰ IGEPAL CA-210 octylphenol ethoxylate is available from Rhone-Poulenc Co., Cranbury, NJ.

¹¹ Experimental Blue III 9495-28 available from Milliken and Company of Spartanburg, South Carolina.

EXAMPLE 4

The Reaction Product of Octylphenol Ethoxylate, Isophorone
Diisocyanate and Blended Black Reactive Colorants

5

About 150.0 grams (0.295 equiv.) of a cyan polymeric reactive colorant¹², about 225.0 grams (0.147 equiv.) of a violet polymeric colorant corresponding to Colorant U from Table I of U.S. Patent No. 5,231,135; about 345.0 (0.552 equiv.) of an orange polymeric reactive colorant corresponding to Colorant B from Table I of U.S. Patent No. 5,231,135; about 450.0 grams (4.054 equiv.) of isophorone diisocyanate¹³ and about 0.18 grams of dibutyltindilaurate catalyst¹⁴ were added to a 3000 ml three-neck resin kettle equipped with a Trubore stirrer, a N₂ atmosphere inlet, and a thermocouple-temperature controller. The reaction mixture was heated to about 90°C with stirring under nitrogen. After 3.5 hours at about 90°C, about 1.0 grams of additional dibutyltindilaurate catalyst¹⁴ and about 805.0 grams (3.012 equiv.) of octylphenol ethoxylate¹⁵ were added and the temperature was raised to about 130°C and held for approximately 3.5 hours. An FT-IR of the product was obtained to insure that all of the isocyanate (NCO) functionality was consumed. The absence (disappearance) of a peak at about 2285 cm⁻¹ (NCO) and the appearance (or increase in magnitude) of peaks at about 1740-1680 cm⁻¹ and about 1540-1530 cm⁻¹ corresponding to urethane frequencies were used to confirm this.

10 The diurethane reaction product was poured into aluminum molds and allowed to cool and harden. This final colored resin product was characterized by the following physical properties: viscosity of about 163.0 cPs as measured by a Ferranti-Shirley cone-plate viscometer at about 140°C, a melting point of below ambient temperature and not measurable by electrothermal melting point apparatus, a T_g of about 3.8°C as measured by differential scanning calorimetry using a DuPont 2100 calorimeter at a scan rate of 20°C/minute, and a spectral strength of about 25 4667 milliliters Absorbance Units per gram at λ max as measured by dilution in n-butanol using a Perkin Elmer Lambda 2S UV/VIS spectrophotometer.

¹² Experimental Blue III 9495-28 available from Milliken and Company of Spartanburg, South Carolina.

¹³ Desmodur I B Isophorone diisocyanate available from Bayer Corp. of Pittsburgh, Pennsylvania.

¹⁴ Dibutyltindilaurate available from Aldrich Chemicals of Milwaukee, Wisconsin.

¹⁵ IGEPAL CA-210 octylphenol ethoxylate is available from Rhone-Poulenc Co., Cranbury, NJ.

EXAMPLE 5

Cyan Ink Made From Amide Wax, Polyethylene Wax, Mixed
Urethane/Urea Resin and Cyan Colored Urethane Resin

5

In a stainless steel beaker were combined about 237.5 grams of the cyan colored resin from Example 3, about 237.5 grams of the reaction product urethane/urea mixture material from Example 2 above, about 473 grams of Witco S-180 stearyl stearamide¹⁶, about 50 grams of polyethylene wax¹⁷ and about 2 grams of Uniroyal Naugard 445 antioxidant¹⁸. The materials 10 were melted together at a temperature of about 125 °C in an oven, then blended by stirring in a temperature controlled mantle at about 125 °C for about one hour. After stirring for about one hour, the cyan ink was filtered through a heated Mott apparatus (available from Mott Metallurgical) using #3 Whatman filter paper and a pressure of about 15 psi. The filtered phase change ink was poured into molds and allowed to solidify to form ink sticks. This final ink 15 product was characterized by the following physical properties: viscosity of about 12.7 cPs as measured by a Ferranti-Shirley cone-plate viscometer at about 140 °C, a melting point of about 89 °C as measured by differential scanning calorimetry using a DuPont 2100 calorimeter, and a T_g of about 21.9 °C as measured by Dynamic Mechanical Analysis using a Rheometrics Solids Analyzer (RSAII). The spectral strength of the ink was determined using a spectrophotographic procedure based on the measurement of the colorant in solution by dissolving the solid ink in 20 butanol and measuring the absorbance using a Perkin Elmer Lambda 2S UV/VIS spectrophotometer. The spectral strength of the ink was measured as about 1469 milliliters Absorbance Units per gram at λ max.

¹⁶ Kemamide S-180 B Stearyl stearamide available from Witco Chemical Company of Memphis, TN.

¹⁷ Polywax 850 B Polyethylene wax available from Petrolite Chemical of Tulsa, Oklahoma.

¹⁸ Naugard 445 B antioxidant available from Uniroyal Chemical Company of Oxford, Connecticut.

EXAMPLE 6

Yellow Ink Made From Amide Wax, Polyethylene Wax, Mixed Urethane/Urea Resin and Yellow Colored Urethane Resin

5

In a stainless steel beaker were combined about 264 grams of the colored resin from Example 1 above, about 225.7 grams of the material from Example 2 above, about 458 grams of Witco S-180 stearyl stearamide¹⁹, about 50 grams of polyethylene wax²⁰ and about 2.0 grams of Uniroyal Naugard 445 antioxidant²¹. The materials were melted together at a temperature of 10 about 125°C in an oven, then blended by stirring in a temperature controlled mantle at about 125°C for about one hour. The yellow ink was then filtered through a heated Mott apparatus (available from Mott Metallurgical) using #3 Whatman filter paper and a pressure of about 15 psi. The filtered phase change ink was poured into molds and allowed to solidify to form ink sticks. This final ink product was characterized by the following physical properties: viscosity of about 12.7 cPs as measured by a Ferranti-Shirley cone-plate viscometer at about 140°C, a melting point of about 90°C as measured by differential scanning calorimetry using a DuPont 2100 calorimeter, and a T_g of about 20°C as measured by Dynamic Mechanical Analysis using a Rheometrics Solids Analyzer (RSAII). The spectral strength of the ink was determined using a spectrophotographic procedure based on the measurement of the colorant in solution by dissolving the solid ink in butanol and measuring the absorbance using a Perkin Elmer Lambda 20 2S UV/VIS spectrophotometer. The spectral strength of the ink was measured as about 1529 milliliters Absorbance Units per gram at λ max.

¹⁹ Kemamide S-180 B Stearyl stearamide available from Witco Chemical Company of Memphis, TN.

²⁰ Polywax 850 B Polyethylene wax available from Petrolite Chemical of Tulsa, Oklahoma.

²¹ Naugard 445 B antioxidant available from Uniroyal Chemical Company of Oxford, Connecticut.

EXAMPLE 7

Black Ink Made from Amide Wax, Polyethylene Wax Mixed Urethane/Urea Resin and Black Colored Urethane Resin

5

In a stainless steel beaker were combined about 220 grams of the colored urethane resin from Example 4 above, about 220 grams of the reaction product urethane/urea mixture material from Example 2 above, about 508 grams of Witco S-180 stearyl stearamide²², about 50 grams of polyethylene wax²³ and about 2.0 grams of Uniroyal Naugard 445 antioxidant²⁴. The materials 10 were melted together at a temperature of about 125 °C in an oven, then blended by stirring in a temperature controlled mantle at about 125 °C for about one hour. The black ink was then filtered through a heated Mott apparatus (available from Mott Metallurgical) using #3 Whatman filter paper and a pressure of about 15 psi. The filtered phase change ink was poured into molds and allowed to solidify to form ink sticks. This final ink product was characterized by the 15 following physical properties: viscosity of about 12.9 cPs as measured by a Ferranti-Shirley cone-plate viscometer at about 140 °C, a melting point of about 89 °C as measured by differential scanning calorimetry using a DuPont 2100 calorimeter, and a T_g of about 16 °C as measured by Dynamic Mechanical Analysis using a Rheometrics Solids Analyzer (RSAII). The spectral strength of the ink was determined using a spectrophotographic procedure based on the measurement of the colorant in solution by dissolving the solid ink in butanol and measuring the absorbance using a Perkin Elmer Lambda 2S UV/VIS spectrophotometer. The spectral strength 20 of the ink was measured as about 1434 milliliters Absorbance Units per gram at λ max.

²² Kemamide S-180 B Stearyl stearamide available from Witco Chemical Company of Memphis, TN.

²³ Polywax 850 B Polyethylene wax available from Petrolite Chemical of Tulsa, Oklahoma.

²⁴ Naugard 445 B antioxidant available from Uniroyal Chemical Company of Oxford, Connecticut.

PRINT AND PERFORMANCE TESTING

The inks in Examples 5, 6, and 7 were tested in a Tektronix Phaser™ 340 printer, which uses an offset transfer printing system. All of the above inks were found to completely transfer
5 and to give images of good color, print quality and durability either as primary colors or when used in combination with each other or the commercially available Phaser™ 340 printer inks.

The inks of Examples 5, 6 and 7 were poured into molded HIPSMA (High Impact Polystyrene/Maleic Anhydride) plastic cups or tubs and allowed to cool and solidify. The finished solid ink sticks from these examples had markedly better surface finishes and better
10 release properties from the plastic cups when compared to comparable formulations without the polyethylene wax additive.

Prints made from these examples showed better blocking resistance at high temperatures when compared to comparable formulations without the polyethylene wax additives. The blocking test used is described on page 56 of the Proceedings of NIP12: The Twelfth
15 International Congress on Digital Printing Technologies, published in 1996 by the Society for Imaging Science and Technology.

096647265 - 090801

EXAMPLE 8

About 500 grams of Petrolite PE850 wax was filtered in a Mott apparatus using Whatman #3 paper. The filtration was done at about 125 °C and 15 psi. The filtered polyethylene wax was 5 poured into aluminum ink molds and allowed to harden in the shape of Phaser™ 300 ink sticks. The wax sticks were placed in the ink reservoir of a Tektronix Phaser™ 300 printer. This printer was used to print a matrix of PE wax dots over the top of images previously made using a Phaser™ 340 printer. The matrix varied from about 1% area coverage to about 20% area coverage. It was found that a matrix of about 5% coverage of wax dots was a good compromise 10 between placing a minimum amount of wax over the image and obtaining good document feeding performance in a photocopier. This overprinting method was effective to enhance the document-feeding performance of prints made with commercial Phaser™ 340 inks, as well as the inks from the aforementioned U.S. Patent Application No. 08/672,815 (now U.S Patent No. 5,830,942), when the output sheets were fed through the automatic document feeder of a number 15 of different model photocopiers, including models made by Xerox, Canon and Minolta.

EXAMPLE 9

Cyan Ink Made From Polyethylene Wax and Compatible Amide Resin

5 In a stainless steel beaker were combined about 89 grams of the material from Example 1 of U.S. Pat. 5,750,604, about 170 grams of the material from Example 1 of U.S. Application 09/354,237, and about 496 grams of Polywax PE655²⁵. The materials were melted together at a temperature of about 135°C in an oven, then blended by stirring in a temperature controlled mantle for ½ hour at 135°C. At that time about 44 grams of a cyan wax from Example 4 of U.S.
10 Pat. 5,919,839 were added along with about 2 grams of an antioxidant²⁶ and the mixture was stirred for an additional two hours. After the ink had mixed, 10 grams of Hyflo Supercel filter aid (available from Fluka Chemical) was added and stirred into the molten ink for five minutes. The ink was then filtered through heated (135°C) Mott apparatus (available from Mott Mettalurgical) using Whatman #3 filter paper at 5 psi. The filtered ink was poured into molds
15 and allowed to solidify to form ink sticks. The viscosity of the finished cyan ink was about 12.0 cPs at 135°C as measured by a Rheometric Scientific RS-2000 cone-plate viscometer. The spectral strength of about 1460 ml*A/g in butanol solution was determined on a Perkin-Elmer Lambda 2S spectrophotometer. The melting point of about 100°C was measured by differential scanning calorimetry using a DuPont 2100 calorimeter. The Tg of about 9°C was measured by dynamic mechanical analysis using a Rheometric Scientific RSA II Solids Analyzer. This ink
20 was placed in a prototype Phaser™ 840 printer which uses an indirect printing process. The ink was printed using a print head temperature of about 135°C. The finished prints were found to have a good color, durability and image quality.

²⁵ Polywax PE655 - Polyethylene wax available from Baker Petrolite Co. of Tulsa, OK.

²⁶ Naugard 445 - antioxidant available from Uniroyal Chemical Company, Inc. of Middlebury, CT 06749.

EXAMPLE 10

Magenta Ink Made From Polyethylene Wax and Compatible Amide Resin

5 In a stainless steel beaker were combined about 93 grams of the material from Example 1 of U.S. Pat. 5,750,604, about 39 grams of the material from Example 4 of U.S. Application 09/400,127, about 185 grams of the material from Example 1 of U.S. Application 09/354,237, about 343 grams of Polywax PE655²⁷ and about 130 grams of stearyl stearamide²⁸. In addition, 1.68 grams of an antioxidant²⁹ was added to the mixture. The materials were melted together at
10 a temperature of about 135°C in an oven, then blended by stirring in a temperature controlled mantle for ½ hour at 135°C. At that time 4.0 grams of Neptun Red Base NB³⁰, 4.0 grams of Keyplast Magenta RB³¹ and 2.0 grams of Bio-Soft S-100³² were added to the mixture and the mixture was stirred for an additional two hours. After the ink had mixed, 10 grams of Hyflo Supercel filter aid (available from Fluka Chemical) was added and stirred into the molten ink for
15 five minutes. The ink was then filtered through a heated (135°C) Mott apparatus (available from Mott Mettalurgical) using Whatman #3 filter paper at 5 psi. The filtered ink was poured into molds and allowed to solidify to form ink sticks. The viscosity of the finished cyan ink was about 11.7 cPs at 135°C as measured by a Rheometric Scientific RS-2000 cone-plate viscometer. The spectral strength of about 880 ml*A/g in butanol solution was determined on a Perkin-Elmer
20 Lambda 2S spectro-photometer. The melting point of about 103°C was measured by differential scanning calorimetry using a DuPont 2100 calorimeter. The Tg of about 10°C was measured by dynamic mechanical analysis using a Rheometric Scientific RSA II Solids Analyzer. This ink was placed in a prototype Phaser™ 840 printer which uses an indirect printing process. The ink was printed using a print head temperature of about 135°C. The finished prints were found to
25 have a good color, durability and image quality.

²⁷ Polywax PE655 - Polyethylene wax available from Baker Petrolite Co. of Tulsa, OK.

²⁸ Kemamide S-180 - stearyl stearamide available from Witco of Memphis, TN 38108.

²⁹ Naugard 445 - antioxidant available from Uniroyal Chemical Co., Inc. of Middlebury, CT 06749.

³⁰ Neptun Red Base NB 543 - a solvent soluble dye available from BASF Corp. of Renesselear, NY.

³¹ Keyplast Magenta RB - a solvent soluble dye available from Keystone Aniline Corp. of Chicago, IL 60093.

³² Bio-Soft S-100 - dodecylbenzenesulfonic acid available from Stepan Co. of Northfield, IL 60093.

EXAMPLE 11

Yellow Ink Made From Polyethylene Wax and Compatible Amide Resin

5 In a stainless steel beaker were combined about 94 grams of the material from Example 1 of U.S. Pat. 5,750,604, about 40 grams of the material from Example 4 of U.S. Application 09/400,127, about 141 grams of the material from Example 1 of U.S. Application 09/354,237, and about 434 grams of Polywax PE655³³. In addition about 40 grams of stearyl stearamide³⁴ and about 2 grams of an antioxidant³⁵, were added to the mixture. The materials were melted
10 together at a temperature of about 135°C in an oven, then blended by stirring in a temperature controlled mantle for ½ hour at 135°C. At that time about 45 grams of the yellow wax from Example 1 of U.S. Pat. 5,919,839 and about 5 grams of a yellow dye³⁶ were added to the mixture and the mixture was stirred for an additional two hours. After the ink had mixed, 10 grams of Hyflo Supercel filter aid (available from Fluka Chemical) was added and stirred into the molten
15 ink for five minutes. The ink was then filtered through a heated (135°C) Mott apparatus (available from Mott Mettallurgical) using Whatman #3 filter paper at 5psi. The filtered ink was poured into molds and allowed to solidify to form ink sticks. The viscosity of the finished yellow ink was about 12.0 cPs at 135°C as measured by a Rheometric Scientific RS-2000 cone-plate viscometer. The spectral strength of about 1304 ml*A/g in butanol solution was determined on a Perkin-Elmer Lambda 2S spectrophotometer. The melting point of about 101°C was measured by differential scanning calorimetry using a DuPont 2100 calorimeter. The Tg of about 12°C was measured by dynamic mechanical analysis using a Rheometric Scientific RSA II Solids Analyzer. This ink was placed in a prototype Phaser™ 840 printer which uses an indirect printing process. The ink was printed using a print head temperature of about 135°C.
20 The finished prints were found to have good color, durability and image quality.
25

EXAMPLE 12

Black Ink Made From Polyethylene Wax and Compatible Amide Resin

³³ Polywax PE655 - Polyethylene wax available from Baker Petrolite Co. of Tulsa, OK.

³⁴ Kemamide S-180 - stearyl stearamide available from Witco of Memphis, TN 38108.

³⁵ Naugard 445 - antioxidant available from Uniroyal Chemical Co., Inc. of Middlebury, CT 06749.

³⁶ Orasol Yellow 2GLN - a solvent soluble dye available from Ciba Specialty Chemicals of Newport, DE 19804-2490.

In a stainless steel beaker were combined about 78 grams of the material from Example 1 of U.S. Pat. 5,750,604, about 26 grams of the material from Example 4 of U.S. Application 09/400,127, about 152 grams of the material from Example 1 of U.S. Application 09/354,237, and about 401 grams of Polywax PE655³⁷. In addition about 91 grams of stearyl stearamide³⁸, 5 about 27 grams of a plasticizer³⁹ and about 2 grams of an antioxidant⁴⁰ were added to the mixture. The materials were melted together at a temperature of about 135 °C in an oven, then blended by stirring in a temperature controlled mantle for ½ hour at 135 °C. At that time 24 grams of a Savinyl Black NS⁴¹ was added to the mixture and the mixture was stirred for an additional two hours. After the ink had mixed, 10 grams of Hyflo Supercel filter aid (available from Fluka 10 Chemical) was added and stirred into the molten ink for five minutes. The ink was then filtered through a heated (135 °C) Mott apparatus (available from Mott Mettalurgical) using Whatman #3 filter paper at 5 psi. The filtered ink was poured into molds and allowed to solidify to form ink sticks. The viscosity of the finished black ink was about 11.5 cPs at 135 °C as measured by a Rheometric Scientific RS-2000 cone-plate viscometer. The spectral strength of about 785 15 ml*A/g in butanol solution was determined in a Perkin-Elmer Lambda 2S spectrophotometer. The melting point of about 101 °C was measured by differential scanning calorimetry using a DuPont 2100 calorimeter. The Tg of about 7 °C was measured by dynamic mechanical analysis using a Rheometric Scientific RSA II Solids Analyzer. This ink was placed in a prototype Phaser™ 840 printer which uses an indirect printing process. The ink was printed using a print 20 head temperature of about 135 °C. The finished prints were found to have a good color, durability and image quality.

³⁷ Polywax PE655 - Polyethylene wax available from Baker Petrolite Co. of Tulsa, OK.

³⁸ Kemamide S-180 - stearyl stearamide available from Witco of Memphis, TN 38108.

³⁹ Santicizer 278 - plasticizer available from Solutia (formerly Monsanto Co. of St. Louis, MO 63167).

⁴⁰ Naugard 445 - antioxidant available from Uniroyal Chemical Co., Inc. of Middlebury, CT 06749.

⁴¹ Savinyl Black NS - solvent soluble black dye available from Clariant Corp. of Coventry, RI 02816.

EXAMPLE 13

The Reaction Product of Hydroabietyl Alcohol and
Isophorone Diisocyanate

5

About 391.9 grams (1.351 moles) of Abitol E hydroabietyl alcohol⁴² was added to a 1000ml four-neck resin kettle equipped with a Trubore stirrer, an N₂ atmosphere inlet, 200 ml addition funnel, and a thermocouple-temperature controller. The kettle was heated to about 100°C with stirring under an N₂ atmosphere and about 150.0 grams (0.676 moles) of isophorone diiso-cyanate⁴³ was added to the addition funnel. About 0.50 grams of dibutyltindilaurate⁴⁴ catalyst was added to the Abitol E, followed by dropwise addition of the isophorone diisocyanate over 3 hours. The temperature was gradually increased to about 155°C during this 3 hour period. After an additional 2 hours at about 155°C, a Fourier Transform Infrared Spectroscopy (FT-IR) of the product was run to insure all of the isocyanate (NCO) was consumed. The absence (disappearance) of a peak at about 2285 cm⁻¹ (NCO) and the appearance (or increase in magnitude) of peaks at about 1740-1680 cm⁻¹ and about 1540-1530 cm⁻¹ corresponding to urethane frequencies were used to confirm this. The final di-urethane resin product was poured into aluminum molds and allowed to cool and harden. This final product was a clear solid resin at room temperature characterized by the following physical properties: viscosity of about 4,072.9 cPs as measured by a Ferranti-Shirley cone-plate viscometer at about 140°C, a melting point of from about 72.0°C to about 76.0°C as measured by an electrothermal capillary melting point apparatus, and a T_g of about 48°C as measured by differential scanning calorimetry using a DuPont 2100 calorimeter at a scan rate of 20°C/minute.

⁴² Abitol E - Hydroabietyl alcohol available from Hercules Inc. of Wilmington, Delaware.

⁴³ Desmodur I - Isophorone Diisocyanate available from Bayer Corp. of Pittsburg, Pennsylvania.

⁴⁴ Dibutyltindilaurate available from Aldrich Chemicals of Milwaukee, Wisconsin.

EXAMPLE 14

The Reaction Product of 1.5 Parts Hydroabietyl Alcohol, 0.5 Parts Octadecyl Amine, and Isophorone Diisocyanate

5

About 240.2 grams (0.676 moles) of hydroabietyl alcohol⁴⁵ was added to a 1000ml four-neck resin kettle equipped with a Trubore stirrer, an N₂ atmosphere inlet, 200 ml addition funnel, and a thermocouple-temperature controller. About 100.0 grams (0.45 moles) of isophorone diisocyanate⁴⁶ was added to the addition funnel. Agitation of the hydroabietyl alcohol first was
10 begun and then all of the isophorone diisocyanate was added over approximately 5 minutes. About 0.22 grams of dibutyltindilaurate⁴⁷ catalyst was added and the reaction mixture heated to about 125°C under an N₂ atmosphere. After 4 hours at 125°C, about 59.95 grams (0.225 moles)
15 of octadecyl amine⁴⁸ was added and the temperature raised to about 150°C and held for approximately 2 hours. An FT-IR of the reaction product was run to insure all of the NCO functionality was consumed. The absence (disappearance) of a peak at about 2285 cm⁻¹ (NCO) and the appearance (or increase in magnitude) of peaks at about 1705-1635 cm⁻¹ and about 1515-1555 cm⁻¹ corresponding to urea frequencies and about 1740-1680 cm⁻¹ and about 1540-1530 cm⁻¹ corresponding to urethane frequencies were used to confirm this. The final mixed urethane/urea
20 resin product was poured into aluminum molds and allowed to cool and harden. This final product was a clear solid resin at room temperature characterized by the following physical properties: viscosity of about 314.8 cPs as measured by a Ferranti-Shirley cone-plate viscometer at about 140°C, a melting point of from about 67.9°C to about 87.0°C as measured by an electrothermal capillary melting point apparatus, and a T_g of about 23°C as measured by differential scanning calorimetry using a DuPont 2100 calorimeter at a scan rate of 20°C/minute.

25

⁴⁵ Abitol E - Hydroabietyl alcohol available from Hercules Inc. of Wilmington, Delaware.

⁴⁶ Desmodur I - Isophorone diisocyanate available from Bayer Corp. of Pittsburgh, Pennsylvania.

⁴⁷ Dibutyltindilaurate available from Aldrich Chemicals of Milwaukee, Wisconsin.

⁴⁸ Octadecyl amine (technical grade) available from ACROS Organics of New Jersey.

EXAMPLE 15

The Reaction Product of 1.25 Parts Hydroabietyl Alcohol,
0.75 Parts Octadecyl Amine and Isophorone Diisocyanate

5

About 150.1 grams (0.422 moles) of hydroabietyl alcohol⁴⁹ and about 75.0 grams (0.338 moles) of isophorone diisocyanate⁵⁰ were added to a 500ml three-neck resin kettle equipped with a Trubore stirrer, an N₂ atmosphere inlet, and a thermocouple-temperature controller. Agitation was begun and then about 0.22 grams of dibutyltindilaurate⁵¹ catalyst was added and the reaction mixture heated to about 130 °C under an N₂ atmosphere. After 4 hours at about 130 °C, about 10 67.45 grams (0.253 moles) of octadecyl amine⁵² was added and the temperature raised to about 150 °C and held for approximately 2 hours. An FT-IR of the reaction product was run to insure all of the NCO functionality consumed. The absence (disappearance) of a peak at about 2285 cm⁻¹(NCO) and the appearance (or increase in magnitude) of peaks at about 1705-1635 cm⁻¹ and about 1515-1555 cm⁻¹ corresponding to urea frequencies and about 1740-1680 cm⁻¹ and about 15 1540-1530 cm⁻¹ corresponding to urethane frequencies were used to confirm this. The final mixed urethane/urea resin product was then poured into aluminum molds and allowed to cool and harden. This final product was a clear solid resin at room temperature characterized by the following physical properties: viscosity of about 275.0 cPs as measured by a Ferranti-Shirley cone-plate viscometer at about 140 °C, a melting point of from about 68.4 °C to about 89.0 °C as measured by an electrothermal capillary melting point apparatus, and a T_g of about 17 °C as measured by differential scanning calorimetry using a DuPont 2100 calorimeter at a scan rate of 20 °C/minute.

20
25

⁴⁹ Abitol E - Hydroabietyl alcohol available from Hercules Inc. of Wilmington, Delaware.

⁵⁰ Desmodur I - Isophorone diisocyanate available from Bayer Corp. of Pittsburg, Pennsylvania.

⁵¹ Dibutyltindilaurate available from Aldrich Chemicals of Milwaukee, Wisconsin.

⁵² Octadecyl amine (technical grade) available from ACROS Organics of New Jersey.

EXAMPLE 16

The Reaction Product of 1 Part Hydroabietyl Alcohol,
1 Part Octadecyl Amine and Isophorone Diisocyanate

5

About 120.1 grams (0.338 moles) of hydroabietyl alcohol⁵³ and about 75.0 grams (0.338 moles) of isophorone diisocyanate⁵⁴ was added to a 500ml three-neck resin kettle equipped with a Trubore stirrer, an N2 atmosphere inlet, and a thermocouple-temperature controller. Agitation was begun and then about 0.22 grams of dibutyltindilaurate⁵⁵ catalyst was added and the reaction mixture heated to about 90°C under an N₂ atmosphere. After 1 hour at about 90°C the temperature was increased to about 110°C and held for 2 hours. About 89.93 grams (0.338 moles) of octadecyl amine⁵⁶ was added and the temperature raised to about 130°C and held for approximately 2 hours. An FT-IR of the reaction product was run to insure all of the NCO functionality was consumed. The absence (disappearance) of a peak at about 2285 cm⁻¹ (NCO) and the appearance (or increase in magnitude) of peaks at about 1705-1635 cm⁻¹ and about 1515-1555 cm⁻¹ corresponding to urea frequencies and about 1740-1680 cm⁻¹ and about 1540-1530 cm⁻¹ corresponding to urethane frequencies were used to confirm this. The final mixed urethane/urea resin product was poured into aluminum molds and allowed to cool and harden. This final product was a clear solid resin at room temperature characterized by the following physical properties: viscosity of about 15.7 cPs as measured by a Ferranti-Shirley cone-plate viscometer at about 140°C, a melting point of from about 73.2°C to about 110°C as measured by an electrothermal capillary melting point apparatus, and a T_g of about 16°C as measured by differential scanning calorimetry using a DuPont 2100 calorimeter at a scan rate of 20°C/minute.

While the invention has been described above with reference to specific embodiments thereof, it is apparent that many changes, modifications and variations can be made without departing from the inventive concept disclosed herein. For example, it should be noted where a urethane reaction product is obtained, a single alcohol precursor or multiple alcohol precursors may be used with an appropriate isocyanate as long as the required stoichiometric ratio is

⁵³ Abitol E - Hydroabietyl alcohol available from Hercules Inc. of Wilmington, Delaware.

⁵⁴ Desmodur I - Isophorone diisocyanate available from Bayer Corp. of Pittsburg, Pennsylvania.

⁵⁵ Dibutyltindilaurate available from Aldrich Chemicals of Milwaukee, Wisconsin.

⁵⁶ Octadecyl amine (technical grade) available from ACROS Organics of New Jersey.

maintained. Similarly, where a urea is the reaction product, a single amine precursor or multiple amine precursors may be employed as long as the required stoichiometric ratio is maintained. Where a urethane/urea reaction product is obtained, single or multiple alcohol and amine precursors may be employed within the appropriate stoichiometric ratios. Accordingly, it is
5 intended to embrace all such changes, modifications and variations that fall within the spirit and broad scope of the appended claims.

000000000000000000000000

WHAT IS CLAIMED IS:

1. A phase change ink composition comprising:

a urethane that is the reaction product of one or more alcohols and one or more

5 isocyanates, the alcohols comprising monohydric fused-ring alcohols; and

at least one polyethylene wax.

2. The phase change ink composition of claim 1 wherein the isocyanates

comprise isophorone diisocyanate.

10

3. The phase change ink composition of claim 1 wherein the monohydric fused-

ring alcohols include one or more of hydroabietyl alcohol, methyl ester of hydrogenated

rosin, and decarboxylated rosin.

15

4. The phase change ink composition of claim 1 wherein the monohydric fused-

ring alcohols include one or more of hydroabietyl alcohol, methyl ester of hydrogenated

rosin, and decarboxylated rosin; and the isocyanates comprise isophorone diisocyanate.

20

5. The phase change ink composition of claim 1 wherein the alcohols consist of

one or more of hydroabietyl alcohol, methyl ester of hydrogenated rosin, and decarboxylated

rosin; and the isocyanates consist of isophorone diisocyanate.

25

6. A phase change ink composition comprising:

a urethane resin that is the reaction product of one or more alcohols and one or more

isocyanates, the alcohols comprising fused-ring alcohols which include at least three fused

rings.

7. The phase change ink composition of claim 6 wherein the fused-ring alcohols

consist of monohydric alcohols.

30

09657236 096500
8. The phase change ink composition of claim 6 wherein the fused-ring alcohols which include at least three fused rings consist of monohydric alcohols.

9. The phase change ink composition of claim 6 wherein the fused-ring alcohols
5 include one or more of hydroabietyl alcohol, methyl ester of hydrogenated rosin, and
decarboxylated rosin.

10. The phase change ink composition of claim 6 wherein the fused-ring alcohols
include one or more of hydroabietyl alcohol, methyl ester of hydrogenated rosin, and
10 decarboxylated rosin; and the isocyanates comprise isophorone diisocyanate.

11. The phase change ink composition of claim 6 wherein the alcohols consist of
one or more of hydroabietyl alcohol, methyl ester of hydrogenated rosin; and decarboxylated
rosin and the isocyanates consist of isophorone diisocyanate.
15

12. A phase change ink composition comprising:
a urethane resin that is the reaction product of one or more alcohols and one or more
isocyanates, the alcohols comprising monohydric fused-ring alcohols having no double
bonds.
20

13. The phase change ink composition of claim 12 further comprising a
polyethylene wax.

14. The phase change ink composition of claim 12 further comprising a
25 polyethylene wax and a mono-amide.

15. The phase change ink composition of claim 12 wherein the monohydric fused-
ring alcohols include alcohols having at least three fused rings.

16. A phase change ink comprising:
a urethane that is the reaction product of one or more alcohols and one or more
isocyanates, the alcohols comprising monohydric fused-ring alcohols;
at least one polyethylene wax; and
5 a colorant.
17. The phase change ink of claim 16 wherein the monohydric fused-ring alcohols
include one or more of hydroabietyl alcohol, methyl ester of hydrogenated rosin, and
decarboxylated rosin.
- 10 18. The phase change ink composition of claim 16 wherein the monohydric fused-
ring alcohols include one or more of hydroabietyl alcohol, methyl ester of hydrogenated
rosin, and decarboxylated rosin; and the isocyanates comprise isophorone diisocyanate.
- 15 19. The phase change ink composition of claim 16 wherein the alcohols consist of
one or more of hydroabietyl alcohol, methyl ester of hydrogenated rosin, and decarboxylated
rosin; and the isocyanates consist of isophorone diisocyanate.
- 20 20. The phase change ink composition of claim 16 wherein the alcohols consist of
one or more of hydroabietyl alcohol, methyl ester of hydrogenated rosin, and decarboxylated
rosin; and the isocyanates consist of isophorone diisocyanate; the ink further comprising a
mono-amide.

21. A method for producing a layer of a phase change ink on a surface of a substrate, which comprises:

forming a phase change ink composition in the solid phase, the phase change ink composition comprising a phase change carrier composition and a colorant material; said phase change carrier composition comprising a urethane resin that is the reaction product of at least one fused ring alcohol and an isocyanate, the fused ring alcohol including at least three fused rings;

melting the ink;

applying the melted ink to at least one surface of a substrate; and
solidifying the applied ink on the surface of the substrate.

22. The method of claim 21 wherein the fused-ring alcohols consist of monohydric alcohols.

23. The method of claim 21 wherein the fused-ring alcohols which include at least three fused rings consist of monohydric alcohols.

24. The method of claim 21 wherein the fused-ring alcohols include one or more of hydroabietyl alcohol, methyl ester of hydrogenated rosin, and decarboxylated rosin.

25. The method of claim 21 wherein the fused-ring alcohols include one or more of hydroabietyl alcohol, methyl ester of hydrogenated rosin, and decarboxylated rosin; and the isocyanates comprise isophorone diisocyanate.

26. The method of claim 21 wherein the alcohols consist of one or more of hydroabietyl alcohol, methyl ester of hydrogenated rosin, and decarboxylated rosin; and the isocyanates consist of isophorone diisocyanate.

27. A method of forming a phase change ink, comprising reacting one or more alcohols with one or more isocyanates, the alcohols comprising fused-ring alcohols which include at least three fused rings.

28. The method of claim 27 wherein the fused-ring alcohols consist of monohydric alcohols.


29. The method of claim 27 wherein the fused-ring alcohols which include at least
5 three fused rings consist of monohydric alcohols.

30. The method of claim 27 wherein the fused-ring alcohols include one or more of hydroabietyl alcohol, methyl ester of hydrogenated rosin, and decarboxylated rosin.

10 31. The method of claim 27 wherein the fused-ring alcohols include one or more
of hydroabietyl alcohol, methyl ester of hydrogenated rosin, and decarboxylated rosin; and
the isocyanates comprise isophorone diisocyanate.

32. The method of claim 27 wherein the alcohols consist of one or more of
15 hydroabietyl alcohol, methyl ester of hydrogenated rosin, and decarboxylated rosin; and the
isocyanates consist of isophorone diisocyanate.


33. A composition comprising:



wherein R₁-R₁₉ comprise hydrogen, alkyl groups or aryl groups, and can be the same as one another or different from one another; wherein one or more of R₁-R₁₉ can be comprised by a ring structure; and wherein X₁ comprises one or more methylene groups.

34. The composition of claim 33 wherein some of R₁-R₁₉ are methyl groups and some of R₁-R₁₉ are not methyl groups, and wherein at least some of R₁-R₁₉ which are not methyl groups are hydrogen.


35. A composition comprising:



wherein R₁-R₃₀ comprise hydrogen, alkyl groups or aryl groups, and can be the same as one another or different from one another; and wherein X₁, X₂ and X₃ comprise one or more methylene groups and can be the same as one another or different from one another.

36. The composition of claim 35 wherein some of R₁-R₃₀ are methyl groups and some of R₁-R₃₀ are not methyl groups, and wherein at least some of the R₁-R₃₀ which are not methyl groups are hydrogen.

37. A composition comprising:




wherein R₁, R₂, R₃, R₄, R₅, R₆, R₇ and R₈ comprise hydrogen, alkyl groups or aryl groups.

5

38. The composition of claim 37 wherein R₁, R₂, R₃, R₄, R₅, R₆, R₇ and R₈ are methyl groups.


39. A phase change ink comprising:



wherein R₁-R₁₉ comprise hydrogen, alkyl groups or aryl groups, and can be the same as one another or different from one another; wherein one or more of R₁-R₁₉ can be comprised by a ring structure; and wherein X₁ comprises one or more methylene groups.

40. The phase change ink of claim 39 wherein some of R₁-R₃₀ are methyl groups and some of R₁-R₃₀ are not methyl groups, and wherein at least some of the R₁-R₃₀ which are not methyl groups are hydrogen.


41. A phase change ink comprising:



wherein R₁-R₃₀ comprise hydrogen, alkyl groups or aryl groups, and can be the same as one another or different from one another; and wherein X₁, X₂ and X₃ comprise one or more methylene groups and can be the same as one another or different from one another.

42. The phase change ink of claim 41 wherein at least some of R₁-R₃₀ are methyl groups and some of R₁-R₃₀ are not methyl groups, and wherein at least some of the R₁-R₃₀ which are not methyl groups are hydrogen.

43. A phase change ink comprising:



wherein R₁, R₂, R₃, R₄, R₅, R₆, R₇ and R₈ comprise hydrogen, alkyl groups or aryl groups.


5

44. The phase change ink of claim 43 wherein R₁, R₂, R₃, R₄, R₅, R₆, R₇ and R₈ are methyl groups.


5 **PHASE CHANGE INK FORMULATION CONTAINING A COMBINATION
OF A URETHANE RESIN, A MIXED URETHANE/UREA
RESIN, A MONO-AMIDE AND A POLYETHYLENE WAX**

ABSTRACT OF THE DISCLOSURE


10 Phase change ink carrier compositions comprising an admixture of (1) at least one urethane resin; and/or (2) at least one mixed urethane/urea resin; and/or (3) at least one mono-amide; and/or (4) at least one polyethylene wax are provided. In addition, a phase change colored ink of such carrier compositions comprising a phase change ink compatible colorant are also provided. Embodiments of the present invention also include methods for producing
15 a layer of the above phase change colored ink on the surface of a substrate by either direct or indirect printing. Such methods also encompassing using a polyethylene wax as an overcoat layer above such a phase change ink layer on a printed substrate.



Abitol E



Isophorone diisocyanate



1 **DECLARATION OF CONTINUATION-IN-PART FOR PATENT APPLICATION**

2 As a below named inventor, I hereby declare that:

3 My residence, post office address and citizenship are as stated below
4 next to my name.

5 I believe I am the original, first and joint inventor of the subject matter
6 which is claimed and for which a patent is sought on the invention entitled:
7 Phase Change Ink Formulation Containing a Combination of a Urethane
8 Resin, a Mixed Urethane/Urearesin, a Mono-Amide and a Polyethylene Wax,
9 the specification of which is attached hereto.

10 This application in part discloses and claims subject matter disclosed in
11 my earlier filed which is a continuation-in-part of U.S. Patent Application
12 Serial No. 09/013,410, filed January 26, 1998; which is a continuation-in-part
13 application of U.S. Patent Application Serial No. 08/672,815 filed on
14 June 28, 1996, now U.S. patent No. 5,830,942. This application is also a
15 continuation in part of U.S. Patent Application Serial No. 09/078,190, filed
16 May 13, 1998, which is a continuation-in-part application of U.S. Patent
17 Application Serial No. 08/672,816 filed on June 28, 1996.

18 I hereby state that I have reviewed and understand the contents of the
19 above identified specification, including the claims.

20 I hereby claim benefit under Title 35, United States Code, §120 in
21 connection with said earlier filed application;

I acknowledge the duty to disclose information known to me to be material to patentability as defined in Title 37, Code of Federal Regulations §1.56, including any such information which became available between the filing date of the prior application and the national or PCT international filing date of this application.

As to the subject matter of this application, which is common to said earlier application, I do not know and do not believe that the same was ever known or used in the United States of America before our invention thereof or patented or described in any printed publication in any country before our invention thereof, or more than one year prior to said earlier application, or in public use or on sale in the United States of America more than one year prior to said earlier application;

The common subject matter has not been patented or made the subject of an inventor's certificate issued before the date of said earlier application in any country foreign to the United States of America on an application filed by me or my legal representatives or assigns more than twelve months prior to said earlier application; and

As to applications for patents or inventor's certificate on the common subject matter filed in any country foreign to the United States of America, prior to said earlier application by me or my legal representatives or assigns, no such applications have been filed.

As to the subject matter of this application which is not common to said earlier application, I do not know and do not believe that the same was ever known or used in the United States of America before our invention thereof or patented or described in any printed publication in any country before our invention thereof, or more than one year prior to this application, or in public use or on sale in the United States of America more than one year prior to this application;

Said non-common subject matter has not been patented or made the subject of an inventor's certificate issued before the date of this application in any country foreign to the United States of America on an application filed by me or my legal representatives or assigns more than twelve months prior to this application; and

As to applications for patents or inventor's certificate on the invention filed in any country foreign to the United States of America prior to this application by me or my legal representatives or assigns, no such applications have been filed.

POWER OF ATTORNEY:

As a named Inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith: David P. Roberts, Reg. No. 23,032; Randy A. Gregory, Reg. No. 30,386; Mark S. Matkin, Reg. No. 32,268;

1 James L. Price, Reg. No. 27,376; Deepak Malhotra, Reg. No. 33,560; Mark W.
2 Hendricksen, Reg. No. 32,356; David G. Latwesen, Reg. No. 38,533; George
3 G. Grigel, Reg. No. 31,166; Keith D. Grzelak, Reg. No. 37,144; James D.
4 Shaurette, Reg. No. 39,833; Frederick M. Fliegel, Reg. No. 36,138; Donald
5 Brent Kenady, Reg. No. 40,045; James E. Lake, Reg. No. 44,854; Bernard
6 Berman, Reg. No. 37,279; John Beck, Reg. No. 22,833; and Denis Robitaille,
7 Reg. No. 34,098.

8 Direct all communications to Bernard Berman, at WELLS, ST. JOHN,
9 ROBERTS, GREGORY & MATKIN P.S., 601 W. First Avenue, Suite 1300,
10 Spokane, WA 99201-3828. Telephone: (509) 624-4276; (PTO Customer No.
11 021567).

12 I hereby declare that all statements made herein of my own knowledge
13 are true and that all statements made on information and belief are believed
14 to be true; and further that these statements were made with the knowledge
15 that willful false statements and the like so made are punishable by fine or
16 imprisonment, or both, under Section 1001 of Title 18 of the United States
17 Code and that such willful false statement may jeopardize the validity of the
18 application or any patent issued therefrom.

1 * * * * *

2 Full name of inventor: Donald R. Titterington, Ph.D.

3 Inventor's Signature: Donald R. Titterington

4 Date: 8/31/00

5 Residence: Tualatin, Oregon

6 Citizenship: U.S.

7 Post Office Address: 10185 S.W. Siletz Drive
Tualatin, OR 97062

8 * * * * *

9 Full name of inventor: Jeffrey H. Banning, Ph.D.

10 Inventor's Signature: JH

11 Date: 8/30/00

12 Residence: Hillsboro, Oregon

13 Citizenship: U.S.

14 Post Office Address: 484 N.E. 16th Ave.
Hillsboro, OR 97124

15

16

17

18

19

20

21

22